THERMAL DEGRADATION AND KINETIC ANALYSIS ON STEMBARK BIOMASS OF Melaleuca cajuputi Powell (GELAM)

MUHAMAD RAZIMIE BIN MANSOR

Final Year Project Report Submitted in Partial Fulfillment of the Requirements for the Degree of Bachelor of Science (Hons.) Chemistry in the Faculty of Applied Sciences Universiti Teknologi MARA

JANUARY 2017

ABSTRACT

THERMAL DEGRATION AND KINETIC ANALYSIS ON STEMBARK BIOMASS OF Melaleuca cajuputi Powell (GELAM)

Melaleuca species (Pokok Gelam) are a potential sources of renewable energy, melaleuca bark can produce the porous carbon materials for hydrogen storage, which is clean energy solution for future transportation. In this research, stembark of Melaleuca cajuputi Powell ware washed with distilled water to remove any contaminant and dirt before dry it at room temperature. After drying, it was shredded into smaller size for process crushed and grinded into powdered form. In pyrolysis process, powdered stembark of Melaleuca cajuputi Powell were investigate in a non-isothermal thermogravimetric analyser (TGA) in order to determine the degradation behavior of powdered stembark. There are two stage present, which first stage due to the elimination of moisture content and small amount of volatile matter compound and second stage is the place where plant biomass (hemicellulos, cellulose and lignin) degrade. The main decomposition of samples occurred between 230 - 387 °C, at heating rate 10 °C/min, corresponds to the degradation of 63.47% of volatile matter. Weight loss of sample, was strongly affected by heating rates. It was found that an increasing in heating rates results in a shift of thermograms to higher temperature. Attenuated Total Reflectance-Fourier Transform Infrared (ATR-FTIR) was performed to determine the possible chemical functional groups present in stembark of Melaleuca cajuputi Powell. From the ATR-FTIR analysis, there were volatile components that found. such as CO, H₂O, O-H, and cyclic and CO₂. Results showed that stem bark of Melaleuca cajuput Powell can be characterized as high volatile matter and low ash components compared to other biomasses. The activation energy of Melaleuca cajuputi Powell, was calculated by using model free FLYNN-WALL-OZAWA (FWO) and Kissinger-Akahira-Sunose (KAS) methods and ranges value were 17.15 - 32.6 kJ/mol and 17.35 - 30.04 kJ/mol, respectively.

TABLE OF CONTENTS

				1
				PAGE
AC	KNOWLEDGEMENTS			iii
TA	BLE OF CONTENTS			iv
LIS	T OF TABLES			vi
LIS	T OF ABBREVEATIONS			vii
ABS	STRACT			viii
ABS	STRAK			xi
				· · · · · · · · · · · · · · · · · · ·
CH	APTER 1: INTRODUCTION			
1.1	Background study			1
1.2	Significance of study			4
1.3	Objectives of study			4
				2. 24
CH	APTER 2: LITERATURE RE	VIEW		
2.1	Thermal degradation on bioma	SS		5
	2.1.1 thermal degradation in	plant biomass		6
	2.1.2 Melaleuca as energy so	urce		9
2.2	Kinetic study on biomass using And Flynn-Wall-Ozawa (FWO	g Kissinger-Akahi	ra-Sunose	(KAS) 10

CHAPTER 3: METHODOLOGY

3.1	Mater	als	13
	3.1.1	Chemicals	13
	3.1.2	Apparatus	13
	3.1.3	Instrument	14
3.2	Sampl	e collection	14
3.3	Sampl	e preparation	14
3.4	Physic	cal Characterization	15
	3.4.1	Thermogravimetric Analysis	15
	3.4.2	Attenuated Total Reflectance Fourier Transform Infrared	16
		Spectroscopy (ATR-FTIR)	
3.5	Kineti	c Analysis	16
	3.5.1	Flynn-Wall-Ozawa method (FWO)	19
	3.5.2	Kissinger-Akahira-Sunose(KAS)	19
	Approximate Analysis		20
3.61	3.6.1	Moisture Content	20
	3.6.2	Volatile Matter Content	21
	3.6.3	Ash Content	21
	3.6.4	Fixed Carbon Content	22

CHAPTER 4: RESULTS AND DISCUSSION				
4.1 Thermal DecompositionCharacterization	23			
4.1.1 Thermogravimetric Analysis of Stem Bark Melaleuca cajuputi Powell	23			
4.2 Kinetics Analysis	28			
4.2.1 The Effect of Heating Rate	28			
4.2.2 Analysis of the Activation Energy	29			
4.3 Attenuated Total Reflectance Fourier Transform Infrared	19 19 19 19 19 19			
Spectroscopy (ATR-FTIR)	34			
4.4 Approximate Analysis	36			
CHAPTER 5: CONCLUSIONS AND RECOMMENDATIONS				
CITED REFERENCES	41			
APPENDICES	46			
CURRICULUM VITAE	55			

v

LIST OF TABLES

TABLE

TITLE

2.1	List of biomass used for the kinetic study to find the activation energy.	12
3.1	Hazard quotient (HQ) for different heavy metals and hazard index (HI) from consumption of herbs	14
4.1	Two stages thermal decomposition of stem bark Melaleuca cajuputi Powell at heating rate 20°C/min	23
4.2	Two stages thermal decomposition of stem bark Melaleuca cajuputi Powell at heating rate 30°C/min	24
4.3	Two stages thermal decomposition of stem bark Melaleuca cajuputi Powell at heating rate 40°C/min	24
4.4	The different sample with different heating rates for final residue left.	27
4.5	the first stage activation energy (Ea) and the correlation factors (R^2) for different conversion values using the FWO and KAS methods.	29
4.6	The second stage activation energy (Ea) and the correlation factor (R^2) for different conversion values using the FWO and KAS methods.	30
4.7	ATR – FTIR result of powdered Melaleuca cajuputi Powell stem bark.	34
4.8	Approximate analysis data for <i>Melaleuca cajuputi</i> Powell stembark.	37