

**VARIATION OF DENSITY AND SPECIFIC GRAVITY  
OF JUVENILE RUBBERWOOD (*Hevea brasiliensis*)  
WITH DIFFERENT HEIGHT LEVEL**

By,

**ILYANI MANSOR**

Final Project Submitted In Partial Fulfillment for the Diploma in Wood Industry  
Faculty of Applied Science  
Universiti Teknologi MARA Pahang  
NOV 2005

## **ACKNOWLEDGEMENT**

Alhamdulillah, glory to Allah, the Almighty for giving me firmness and opportunity to accomplish this project.

Firstly, I'm proud to ventilate my deepest appreciation and earnest gratitude to my advisor, Prof. Dr. Suhaimi Muhammed for his guidance and for all the knowledge that he had furnished me. He had encouraged me to do the best for my thesis project.

Special thanks to my family especially my beloved mom, for her support. Without them, I will not have the strength to face with every single problem that occurs during my project. Not to forgot, my dearest, thank you for your understanding.

Lastly, to all my nice friends out there, thank you for your co-operation. May Allah bless us in our daily life.

## TABLE OF CONTENT

|  | Page        |
|--|-------------|
| <b>APPROVAL SHEET</b> .....                                | <b>i</b>    |
| <b>DEDICATION</b> .....                                    | <b>ii</b>   |
| <b>ACKNOWLEDGMENT</b> .....                                | <b>iii</b>  |
| <b>LIST OF TABLES</b> .....                                | <b>vi</b>   |
| <b>LIST OF FIGURES</b> .....                               | <b>vii</b>  |
| <b>LIST OF PLATES</b> .....                                | <b>viii</b> |
| <b>LIST OF ABBREVIATION</b> .....                          | <b>ix</b>   |
| <b>ABSTRACT</b> .....                                      | <b>x</b>    |
| <b>ABSTRAK</b> .....                                       | <b>xi</b>   |
| <br><b>CHAPTER</b>   |             |
| <br><b>1.0 FOREWORD</b>                                    |             |
| 1.1 Introduction of Density and Specific Gravity .....     | 1           |
| 1.2 Prelude of Juvenile Rubberwood .....                   | 2           |
| 1.3 Objectives .....                                       | 3           |
| <br><b>2.0 LITERATURE REVIEW</b>                           |             |
| 2.1 Interpretation of Density and Specific Gravity.....    | 4           |
| 2.1.1 Importance of Density.....                           | 6           |
| 2.1.2 Essential of Specific Gravity.....                   | 7           |
| 2.2 Rubberwood.....  | 8           |
| 2.2.1 General Characteristics.....                         | 8           |
| 2.2.2 Physical and Mechanical Properties of Rubberwod..... | 10          |
| 2.2.3 Uses .....   | 12          |

### **3.0 MATERIAL AND METHODS**

|  |    |
|--|----|
| 3.1 Preparation Raw Material .....       | 13 |
| 3.2 Wood Density Determination .....     | 16 |
| 3.3 Specific Gravity Determination ..... | 19 |

### **4.0 RESULT AND CONCLUSION**

|  |    |
|--|----|
| 4.1 The Effect of Rubberwood Density .....         | 22 |
| 4.2 The Effect of Ruberwood Specific Gravity ..... | 24 |

|                             |    |
|-----------------------------|----|
| <b>5.0 CONCLUSION</b> ..... | 26 |
|-----------------------------|----|

|                         |    |
|-------------------------|----|
| <b>REFERENCES</b> ..... | 27 |
|-------------------------|----|

|                         |    |
|-------------------------|----|
| <b>APPENDICES</b> ..... | 28 |
|-------------------------|----|

|                   |    |
|-------------------|----|
| <b>VITA</b> ..... | 36 |
|-------------------|----|

**VARIATION OF DENSITY AND SPECIFIC GRAVITY OF RUBBERWOOD  
(*Hevea brasiliensis*) FOR DIFFERENT HEIGHT LEVEL**

By

Ilyani Mansor

NOVEMBER 2005

**ABSTRACT**

The study of density and specific gravity variation was performed on Rubberwood (*Hevea brasiliensis*). Specific gravity was determined using the maximum moisture content method and density is known as slugs per cubic meter. The samples were examined from three different altitude of a tree – base, middle and top. The result point out that the density was highest at the base, lowest at the middle and a little increase at the top portion. While for specific gravity, the value decrease from base to top part. Hence, specific gravity is related to different height level.