

**ALCOHOL – BENZENE SOLUBLES OF MEMPENING (*Lithocarpus Spp*)  
ACCORDING TO DIFFERENT PORTION OF TREE HIGH AND BETWEEN  
SAPWOOD AND HEARTWOOD**

**BY**

**AHMAD SUHAIMIE BIN MD. NOOR**

**Final Project Submitted in Partial Fulfillment for the Diploma in Wood Industries,  
Faculty of Applied Science,  
Universiti Teknologi MARA Pahang**

**March 2004**

## TABLE OF CONTENTS

<b>APPROVAL SHEET</b> .....	<b>i</b>
<b>DEDICATION</b> .....	<b>ii</b>
<b>ACKNOWLEDGEMENT</b> .....	<b>vi</b>
<b>LIST OF TABLES</b> .....	<b>vii</b>
<b>LIST OF FIGURES</b> .....	<b>viii</b>
<b>LIST OF PLATES</b> .....	<b>ix</b>
<b>ABSTRACT</b> .....	<b>x</b>
<b>ABSTRAK</b> .....	<b>xi</b>

### CHAPTER

#### **I INTRODUCTION**

1.1 Introduction .....	1-2
1.3 Objectives .....	2

#### **II LITERATURE REVIEW**

2.1 Moisture Content .....	3
2.2 Differences between sapwood and heartwood .....	3-5
2.3 Extractive in wood .....	5-6
2.4 Fats and Waxes .....	6
2.5 Phenolic Constituents .....	7

2.6	Characteristic of Mempening .....	7
2.6.1	Vernacular names .....	7
2.6.2	Origin and geographic distribution .....	8
2.6.3	Uses .....	8
2.6.4	Properties .....	9
2.6.5	Description .....	10
2.6.6	Wood anatomy .....	11
2.6.7	Ecology .....	12
<b>III</b>	<b>MATERIAL AND METHOD</b>	
3.1	Material and preparation .....	13-16
3.2	Methodology (Laboratory Method) .....	17
3.2.1	Determination of Moisture Content .....	17-19
3.2.2	Determination of Alcohol – Solubility of Wood .....	20-21
<b>IV</b>	<b>RESULTS AND DISCUSSION</b>	
4.1	Moisture Content (%) .....	22
4.2	Alcohol – Solubility (%) .....	23-26
<b>V</b>	<b>CONCLUSION</b> .....	<b>27</b>
	<b>REFERENCESS</b> .....	<b>28</b>

## ACKNOWLEDGEMENT

First of all, I would like to express my sincere thanks to Almighty ALLAH S.W.T for his blessing and favor in guiding me towards the completion of this final project paper.

To my respectful advisor, Assoc. Professor Dr. Suhaimi Bin Muhammad appreciation for his comment, suggestion, advice and understanding towards in this final project paper. Beside that, Mr. Amran Bin Shafie for his information especially about my project.

This appreciation also due to my group friends under Assoc. Professor Dr. Suhaimi Bin Muhammad especially Nordiana, Shafawati, Syahzulkhikim and Mohd. Azhar for their cooperation and helps during project preparation.

I will never forget for any individual that always give their support to me. May ALLAH S.W.T bless you. Thank you very much.

## **ABSTRACT**

**ALCOHOL – BENZENE SOLUBLES OF MEMPENING (*Lithocarpus Spp*)  
ACCORDING TO DIFFERENT PORTION OF TREE HIGH AND BETWEEN  
SAPWOOD AND HEARTWOOD**

**BY**

**AHMAD SUHAIMIE BIN MD. NOOR**

**MARCH 2004**

Mempening or *Lithocarpus spp* was subjected to chemical analysis involving samples taken at various high and portion. 2 samples from Mempening tree were tested to know the variation of extraneous component in this species. 2 different high are from base and 80% of bole high. Furthermore, samples are also taken in different portion; sapwood and heartwood. The extractives were found to be higher at lower part and in heartwood.