

ASH AND LIGNIN CONTENT OF JUVENILE RUBBERWOOD
(*HEVEA BRASILENSIS*)

NOR AZURA BINTI NORDIN

DIPLOMA IN WOOD INDUSTRY
UNIVERSITI TEKNOLOGI MARA

2005

ACKNOWLEDGEMENT

First of all, I would like to thank almighty ALLAH for His Blessing leading to the success of this final project.

I would like to thank many of my lovely friends for helping me in the preparation of raw material. Also not to forget those who give advise during this thesis completion.

Thank is also due to Cik Junaiza for providing raw material in my study and to Prof Dr Suhaimi for helping me in this thesis write-up and to Mr Rudaini for the help rendered during chemical analysis.

Thank you very much.

TABLE OF CONTENT

TABLE	PAGE
APPROVAL SHEET.....	ii
DEDICATION.....	iii
ACKNOWLEDGEMENT.....	v
TABLE OF CONTENT.....	vi
LIST OF FIGURE.....	viii
ABSTRAK.....	ix
ABSTRACT.....	x
CHAPTER 1	
1.0 INTRODUCTION	
1.1 General.....	1
1.2 Objective.....	2
CHAPTER 2	
2.0 LITERATURE REVIEW	
2.1 Physionogomy.....	3
2.2 Silviculture	4
2.3 Working qualities.....	5
2.4 Uses.....	5
CHAPTER 3	
3.0 MATERIAL AND METHOD	
3.1 Material preparation.....	6

3.2 Determination of moisture content.....	8
3.3 Determination of alcohol benzene solubility.....	9
3.4 Determination of lignin.....	11
3.5 Determination of ash.....	14
CHAPTER 4	
RESULT AND DISCUSSION.....	16
CHAPTER 5	
CONCLUSION AND RECOMMENDATION.....	20
REFERENCES.....	21
APPENDIX.....	22
VITA.....	31

ABSTRACT
ASH AND LIGNIN CONTENT OF RUBBERWOOD
(*HEVEA BRASILENSIS*)

BY
NOR AZURA BT NORDIN

ABSTRACT

The percentage of ash and lignin content in Juvenile Rubberwood according to difference the height level of tree. These results were in accordance the TAPPI standard. , The ash content was state higher top 0.55% and lignin was higher at the bottom with 31.97%. These values for lignin and ash fall within acceptable range. It is important in paper process that is must removed because it can make a quality paper and color reaction can occur when reaction with sun. Besides, the papers become more brittle.