

UNIVERSITI TEKNOLOGI MARA

**STUDIES ON PROTON EXCHANGE
MEMBRANES-BASED SPEEK-
CHITOSAN CROSSLINKED VIA
ULTRAVIOLET CURING METHOD**

NAZLI BIN AHMAD AINI

Thesis submitted in fulfillment
of the requirements for the degree of
Doctor of Philosophy

Faculty of Applied Sciences

March 2018

AUTHOR'S DECLARATION

I declare that the work in this thesis was carried out in accordance with the regulations of Universiti Teknologi MARA. It is original and is the results of my own work, unless otherwise indicated or acknowledged as referenced work. This topic has not been submitted to any other academic institution or non-academic institution for any degree or qualification.

I, hereby, acknowledge that I have supplied with the Academic Rules and Regulations for Post Graduate, Universiti Teknologi MARA, regulating the conduct of my study and research.

Name of Student : Nazli Bin Ahmad Aini
Student I.D. No. : 2008317253
Programme : Doctor of Philosophy - AS990
Faculty : Applied Sciences
Thesis Title : Studies On Proton Exchange Membranes-Based
SPEEK-Chitosan Crosslinked Via Ultraviolet Curing
Method.

Signature of Student :
Date : March 2018

ABSTRACT

The use of proton exchange membrane (PEM) is very significant component in PEMFC and DMFC. It functions to separate anode and cathode, prevents fuel gas crossover, and transports protons from anode to the cathode through it. Nafion is widely used as a PEM material in commercial PEMFC due to high proton conductivity, good mechanical, chemical stability and excellent thermal stability. However, seeking for new materials as an alternative to Nafion is needed due to its expensive, low proton conductivity when temperature operation above 100 °C and high fuel permeability. As an alternative, sulfonated poly(ether ether ketone) (SPEEK) based membrane is a potential candidate due to low cost, exhibit good chemical and thermal stabilities. However, SPEEK with high degree of sulfonation (DS) exhibits gradually deterioration of the mechanical properties, excessive water uptakes at elevated temperatures and methanol permeability that leads to the reduction in cell voltage performance. The use of hybrid membrane is one opportunity to overcome the SPEEK drawbacks. SPEEK and Chitosan can be crosslinked through sulfonic (-SO₃H) and amine (-NH₂) functional groups. Introduction of Chitosan into SPEEK membrane can modify SPEEK properties particularly by improving its swelling ability. Several series of cross-linked membranes of SPEEK with a chitosan were prepared by solution cast technique. SPEEK and Chitosan was dissolved in DMSO and acetic acid, respectively. They were then mixed together and stirred until homogenous solution obtained. The solution was then exposed and treated under ultra violet (UV) light for curing process. Only six samples were prepared with different composition. The composition are pure SPEEK, 90 % SPEEK with 10 % Chitosan, 80 % SPEEK with 20 % Chitosan, 70 % SPEEK with 30 % Chitosan, 60 % SPEEK with 40 % Chitosan and 50 % SPEEK with 50 % Chitosan. The membranes were then characterized by evaluating physical properties, physicochemical properties, thermal properties and electrical properties. Physical properties were analyzed through the results of DS, Fourier transform infrared (FTIR), X-Ray diffractogram (XRD) and surface morphology. The best composition of SPEEK with 74.2 % DS was successfully prepared. The FTIR study revealed considerable interaction between the sulfonic acid functions of SPEEK and amino groups of chitosan. No defects were observed on cross-section surface morphology. Physicochemical properties were analyzed through the results of water uptake, degree of swelling and ion exchange capacity (IEC). The results show that water uptake decreases with increasing of chitosan content from 52 % to 29 %. While, IEC decreases from 0.188 to 0.018 mequi. Thermal properties were studied using the results of TGA and DSC. Results showed that there is not much effect can be seen on both TGA and DSC trend. Characterizations of proton conductivity and transference number were conducted to further study electrical properties of the membranes. It is found that activation energy increases from 10.6 to 90.9 kJ/mol, while proton conductivity of the membranes decreases from 8.51×10^{-3} to $2.85 \times 10^{-7} \text{ Scm}^{-1}$. Ionic transference numbers are found to be in the range of 0.81 to 0.94, indicating the conductor species in the electrolyte membrane system is predominantly ionic. The results from characterizations showed that the optimum sample which is 10 % Chitosan with 90 % SPEEK might be as a good potential candidate to modify the SPEEK properties.

TABLE OF CONTENTS

	Page
CONFIRMATION BY PANEL OF EXAMINERS	ii
AUTHOR'S DECLARATION	iii
ABSTRACT	iv
ACKNOWLEDGEMENT	v
TABLE OF CONTENTS	vi
LIST OF TABLES	x
LIST OF FIGURES	xi
LIST OF ABBREVIATIONS	xiv
CHAPTER ONE: INTRODUCTION	1
1.1 Research Background	1
1.2 Statements of the problem	3
1.3 Objectives	4
1.4 Scope of the Study	4
1.5 Significance of the research	5
1.6 Thesis organization	6
CHAPTER TWO: LITERATURE REVIEW	7
2.1 Introduction	7
2.2 Basic working principle of fuel cells	8
2.2.1 Hydrogen Oxidation	9

2.2.2	Oxygen Reduction	10
2.3	Types of the Fuel Cells	11
2.3.1	Alkaline Fuel Cell (AFC)	14
2.3.2	Polymer Electrolyte Membrane Fuel Cell (PEMFC)	17
2.3.3	Direct Methanol Fuel Cell (DMFC)	20
2.3.4	Phosphoric Acid Fuel Cell (PAFC)	24
2.3.5	Molten Carbonate Fuel Cell (MCFC)	25
2.3.6	Solid Oxide Fuel Cell (SOFC)	27
2.4	Why Polymer Electrolyte Membrane Fuel Cell (PEMFC)	34
2.5	Ion Exchange Membrane / polymer electrolyte	37
2.6	Sulfonated Poly(Ether Ether) Ketone polymer (SPEEK)	39
2.7	Chitosan	41
2.8	Ultraviolet radiation	44
2.9	Crosslinking Membranes	45
2.10	Chapter Summary	47
CHAPTER THREE: METHODOLOGY		49
3.1	Introduction	49
3.2	List of Materials	50
3.3	Sample Preparation	50
3.3.1	Sulfonation Process	51
3.3.2	Irradiated Membrane Preparation	53
3.4	Sample Characterization	55
3.4.1	Degree Of Sulfonation	55
3.4.2	Fourier Transform Infrared	57