

UNIVERSITI TEKNOLOGI MARA

**NANOSTRUCTURED TUNGSTEN
TRIOXIDE ON INTERDIGITATED
MICRO-ELECTRO-MECHANICAL
PLATFORM FOR ETHYLENE GAS
SENSOR APPLICATIONS**

AMIRUL BIN ABD RASHID

Thesis submitted in fulfilment
of the requirements for the degree of
Doctor of Philosophy

Faculty of Mechanical Engineering


September 2016

AUTHOR'S DECLARATION

I declare that the work in this thesis/dissertation was carried out in accordance with the regulations of Universiti Teknologi MARA. It is original and is the results of my own work, unless otherwise indicated or acknowledged as referenced work. This thesis has not been submitted to any other academic institution or non-academic institution for any degree or qualification.

I, hereby, acknowledge that I have been supplied with the Academic Rules and Regulations for Post Graduate, Universiti Teknologi MARA, regulating the conduct of my study and research.

Name of Student : Amirul Bin Abd Rashid
Student I.D. No. : 2011650432
Programme : Doctor of Philosophy-EM990
Faculty : Mechanical Engineering
Thesis : Nanostructured Tungsten Trioxide on
Interdigitated Micro- Electro-Mechanical
Platform for Ethylene Gas Sensor Applications

Signature of Student : 

Date : September 2016

ABSTRACT

In this study, tungsten trioxide (WO_3) nanostructure material is integrated onto interdigitated (IDE) Micro-electro-mechanical (MEMS) platform to form a gas sensor targeting to detect ethylene gas. Traditionally, ethylene gas detection requires the sample of the gas to be collected and measured offline due to the complexity of the measurement system. Even though a newer detection technology which enables for in-situ detection has been developed, the size of the sensor is relatively bulky and very expensive hence it is not suitable for mass outdoor applications examples in the agriculture industry. Therefore, this research explores a different approach to detecting ethylene gas utilizing WO_3 nanostructure as the sensing element of the sensor. This n-type metal oxide family were recognized for its excellent in sensitivity, ruggedness, versatility and relatively low cost to fabricate compared to other gas sensing material technology. The early work in this research is focused on producing one-dimensional WO_3 nanostructure through hydrothermal method. Design of experiment (DOE) technique is used to identify the effect and relationship of the variables in producing WO_3 nanostructure morphology. Field Emission Scanning Electron Microscopy (FESEM) reveals one dimensional, two dimensional and three-dimensional nanostructures have been produced by this facile process. Since the response of the gas sensor is highly dependent on the surface area, the analysis of DOE was focused on defining parameters that will produce one-dimensional nanostructure because it will give the biggest surface to volume ratio compared to the other structures. This type of morphology is also suitable to create the electrical interconnection in between the IDE electrodes to functionalist the sensor. To fabricate the sensor, the synthesized WO_3 nanostructures were deposited on IDE platform to create the conduction network between the electrodes. Three deposition approaches have been explored namely in situ growth, drop cast and spin coating process. A dedicated test rig system is employed to perform the functionality testing for the sensor. The changes of sensor resistance value upon exposed to a certain concentration of ethylene gas at room temperature were then recorded to determine sensor performance. It was concluded that the density and the morphology variations of nanostructure network play a major role in sensitivity, response and recovery time of the sensor. The best sensitivity calculated based on the resistance ratio before and after the sensor exposed to ethylene gas was 1.23 at 20 ppm obtained from sensor fabricated by spin coat fabricated sensor. At the same ethylene concentration value, the sensitivity for drop cast and in situ fabrication process are much lower at 1.05 and 1.04 respectively. In terms of response behaviour, spin coat sensor exhibits fastest response and recovery (7 minutes and 13 minutes) as compared to spin coat process (14 minutes and 28 minutes) and in situ process (10 minutes and 16 minutes). This study contributes the knowledge of controlled hydrothermally synthesis of WO_3 and at the same time proves that the fabricated NANO/MEMS sensor platform are able to detect ethylene gas. This finding is significant in developing ultra-sensitive, small in size and requires low power consumption ethylene gas sensor, especially for precision agricultural applications.

TABLE OF CONTENTS

	Page
CONFIRMATION BY PANEL OF EXAMINERS	ii
AUTHOR'S DECLARATION	iii
ABSTRACT	iv
ACKNOWLEDGEMENT	v
TABLE OF CONTENTS	vi
LIST OF TABLES	ix
LIST OF FIGURES	xi
LIST OF PLATES	xiii
LIST OF SYMBOLS	xvi
LIST OF ABBREVIATIONS	xvii
CHAPTER ONE: INTRODUCTION	1
1.1 Research Background	1
1.2 Ethylene Gas	5
1.3 Precision Agriculture	8
1.4 Problem Statement	9
1.5 Objectives	11
1.6 Scope of The Research	11
1.7 Significance of The Research	12
1.8 Thesis Organization	13
CHAPTER TWO: LITERATURE REVIEW	17
2.1 Introduction	17
2.2 Precision Agriculture Development	17
2.3 Nanotechnology in Agriculture	18
2.4 Ethylene Detection Overview	21
2.4.1 Gas Chromatography (GC) Detection	22
2.4.2 Optical System	23
2.4.3 Electrochemical Sensing	24
2.4.3.1 Amperometric Sensors	24

2.4.3.2	Chemoresistive Sensors	25
2.4.3.3	Capacitive Sensor	26
2.4.4	Comparison of Ethylene Detection Technology	27
2.5	Metal Oxide as Sensor Element	28
2.6	Metal Oxide Nanomaterials	30
2.7	Nanostructured Material (NSM's) Classification	31
2.7.1	Zero-dimensional (0D) NSMs	32
2.7.2	One-dimensional (1D) NSM's	32
2.7.3	Two-dimensional (2D) NSM's	33
2.7.4	Three-dimensional (3D) NSM's	34
2.8	Effect of Nanostructure Morphology to Gas Sensing Properties	35
2.9	Nanostructure Synthesis Method	37
2.10	Hydrothermal Synthesis	40
2.11	Nanostructure Deposition Techniques	41
2.11.1	Liquid Phase Deposition (LPD)	41
2.11.2	Chemical Vapor Deposition (CVD)	43
2.11.3	Physical Vapor Deposition (PVD)	44
2.12	Summary	45
 CHAPTER THREE: THE SYNTHESIS OF TUNGSTEN TRIOXIDE		
3.1	Introduction	47
3.2	WO ₃ Nanostructure Synthesis via Hydrothermal Process	47
3.3	Synthesis Optimization via Design of Experiment (DOE)	52
3.4	Characterization of 1D WO ₃ Nanostructure Material	57
3.4.1	Transmission Electron Microscopy (TEM)	58
3.4.2	X-ray Diffraction (XRD)	61
3.4.3	Raman Spectroscopy	62
3.5	Summary and Discussion	63
 CHAPTER FOUR: SENSOR FABRICATION		
4.1	Introduction	64
4.2	IDE Platform Design Overview	64
4.3	IDE Metal Selection	66