UNIVERSITI TEKNOLOGI MARA

EFFECTS OF HIGH TEMPERATURE ON FORMALDEHYDE AND ANTIMONY LEVELS IN POLYETHYLENE TEREPHTHALATE (PET) BOTTLED MINERAL WATER

NUR SUHAILA BINTI MOHD PILUS

Project paper submitted in partial fulfillment of the requirements

for the degree of

Bachelor in Environmental Health and Safety (Hons.)

Faculty of Health Sciences
JULY 2013

Declaration by Student

Project entitled "Effects of high temperature on formaldehyde and antimony levels in Polyethylene Terephthalate (PET) bottled mineral water is a presentation of my original research work. Wherever contributions of others are involved, every effort is made to indicate this clearly, with due reference to the literature, and acknowledgement of collaborative research and discussions. The project was done under the guidance of Assoc. Prof. Dr. Hazilia binti Hussain as Project Supervisor. It has been submitted to the Faculty of Health Sciences in partial fulfillment of the requirement for the Degree of Bachelor in Environmental Health and Safety (Hons.)

Student's Signature
Nur Suhaila Binti Mohd Pilus
2010825404
890626-05-5052
Date:

ACKNOWLEDGEMENT

Alhamdulillah, thanks to Allah SWT with His blessing and wisdom for giving me guidance to complete this final year project and also for making all the things possible. Without His permission and guidance this thesis would not have been finished. I wish to express my sincere thanks and gratitude to my project supervisor, Assoc. Prof. Dr. Hazilia Binti Hussain for her guidance, advices, patience, ideas, support and comments throughout the preparation of this final year project thesis. Without her valuable assistance this thesis could have not been completed. Her experience and knowledge give me full inspiration to finish this project. I also take this opportunity to extend my deepest appreciation to Coordinator Department of Environmental Health and Safety, Dr Subramaniam A/L Karuppannan who has been assigned to administer this program for his support and commitment in preparation and completion of this project. I also wish to thank for all lecturers concerned, especially lecturers of the Faculty of Environmental Health and Safety for their constructive comments, advice and participation. Finally, deepest and undivided appreciation to my lovely parents En. Mohd Pilus b. Hi Abd Kadir and Pn. Khamsiah binti Mohd Zain, my siblings, my friends especially for Nurul Syuhada Abdullah, Nor Azura binti Sha'ari, Julaina Che Kamal, Nur Husna Sabri, Nur Munirah Mustafa and also Syairah Zahidi Baki, and lab assistants, who had given me inspiration and moral support to complete this final year project and their willingness to sacrifice their leisure time together throughout completing this project.

TABLE OF CONTENTS

TITL	E PAGE				
ACKNOWLEDGEMENT					
TABLE OF CONTENTS					
LIST OF TABLES LIST OF FIGURES LIST OF APPENDICES LIST OF ABBREVIATION		vi vii viii ix			
			ABS	TRACT	xi-xii
	PTER ONE: INTRODUCTION				
1.1	Introduction	1-2			
1.2	Problem Statement	2-3			
1.3	Study Justification	3			
1.4	Study Objectives	4			
	1.4.1 General Objectives				
	1.4.2 Specific Objectives				
	1.4.3 Research question				
1.5	Study Hypothesis	5			
1.6	Conceptual Framework	6			
1.7	Operational Framework	7			
1.8	Conceptual and Operational Definitions	8			
CHAF	PTER TWO: LITERATURE REVIEW				
2.1	Synthesis of PET	9-10			
2.2	Products generation during PET synthesis	10			
2.3	The manufacture of PET bottle	10			
2.4	Types of recycling plastic	11-12			
2.5	Traces of metal: Antimony	12			
2.6	Health effect of Antimony	13			

Abstract

Effects of High Temperature on Formaldehyde and Antimony Levels in Polyethylene Terephthalate (PET) Bottled Mineral Water

Nur Suhaila Binti Mohd Pilus

INTRODUCTION: Mineral water is one of the popular choice for all. Occasionally, this bottle of mineral water would be left in a hot car and would result in the leaching of metal such antimony and carbonyl compound such formaldehyde. OBJECTIVE: The aim of this study were to determine the levels of formaldehyde and antimony in mineral water bottle (PET) due to in-car storage exposure and it health impact to public. METHODOLOGY: The data were collected regarding on the concentration of formaldehyde and antimony in the PET mineral water bottle for one and two weeks exposure. Those sample were stored in the car for two weeks. The concentration for both compound also been tested before storage. Besides that, the storage temperature factor also been taken over time which three times per day until the study was done. The GFAAS and UV-VIS were used for analyzed the concentration of antimony and formaldehyde respectively. The quantitative risk assessment was used for health risks analysis. FINDINGS. The mean concentration for formaldehyde slightly increased the in-car storage duration which are before storage, one week storage and two week storage for each brands. It aslo been proven that the leaching happened after the samples were stored in the car as there is no result before storage. However, all results were below the WHO standard which is 0.9mg/L. The formaldehyde concentration and different storage duration only have a fair correlation (r=0.502) while poor correlation (r=0.214) between the formaldehyde concentration and different brands. The antimony also below the WHO standard; 0.02mg/L. Nonetheless, the mean concentration of antimony was slightly increased by the in-car storage duration which are before storage, one week storage and two week storage for each brands same like formaldehyde. The antimony concentration and different storage duration only have a poor correlation (r=0.228) while poor correlation (r=0.071) between the antimony concentration and different brands. CONCLUSION: There are few factors that could cause the leaching which are temperature, sunlight irradiation, storage duration and the influence of the manufacturing technology and bottling process. The migration of this leaching compound may cause potential effect to consumer.

Keywords: Leaching, formaldehyde, antimony, health risk assessment