

UNIVERSITI TEKNOLOGI MARA

**STUDIES OF BIODEGRADABLE
PROPERTIES OF STARCH BASED
FILM AS POLYBAG FOR
AGRICULTURAL APPLICATION**

MOHD FARHAN BIN AB AZIZ

Thesis submitted in fulfillment
of the requirements for the degree of
Doctor of Philosophy

Faculty of Applied Science

September 2017

ABSTRACT

Plastic have many advantages including good water resistance, ease of processing and low cost. The problem with plastic bag is that, it has great environmental impact as millions of plastic wastes were discarded. Polybag for example can take up from 500 to 1000 years to decay or degrade in agricultural farm which can create serious environmental pollution. The purpose of this study was to investigate the degradable properties of Liner Low Density Polyethylene (LLDPE) filled with Sago SS (SS) and Polyvinyl Alcohol (PVOH). Two processing stage were performed in this research. The first stage covers the preparation and testing on properties of Hybrid Master Batch (MB) film of SS/PVOH formulation. Hybrid MB films were formulated by varying ratios of maximum SS/PVOH of 70%. The second stage covers the preparation and testing of Hybrid Blend Film (BF) of SS/PVOH. For the first stage, combination of LLDPE, SS and PVOH first compounded using twin screw extrusion and fabricated into Hybrid MB films with fixed amount of LLDPE with SS and PVOH varies between 10% to 60%. The Hybrid MB films then test for their tensile properties (ASTM D-1780), Water Absorption (ASTM D-570-95) and Thermal Properties (ASTM D 3418) and Biodegradability (ASTM D5338-98). Tensile properties test shows that increasing the amount of SS in LLDPE films will reduce the tensile strength of the blends as Hybrid MB A exhibited the highest tensile strength of 6.7 MPa while lowest strength was found for Hybrid MB E of 5.1 MPa corresponding to highest starch content of 60% and PVOH 10%. Increasing water absorption of Hybrid MB films were observed with increasing of SS amount in SS/PVOH formulation. Degradability of Hybrid MB films after soil burial for 30 days were observed to be increased with increasing amount of SS due to enzymatic attack of microorganism on the film. DSC result had shown films filled with higher amount of SS exhibited reduction in the melting temperature of the blends. For second stage experimental, Hybrid BF were fabricated using film blowing extrusion and formulated employing 10% Hybrid MB with PE resin and then tested for Carbon Dioxide (CO₂) Measurement (ASTM D 6400), Soil Burial (ASTM D 5338-98), Fourier Transform Infrared Spectroscopy (FTIR – ASTM 1252-98) and Scanning Electron Microscope (SEM). Hybrid blend films were exposed to free Carbon Dioxide atmosphere for 45 days, whereas Soil Burial test was carried out for 1 year. Increasing SS amount on LLDPE films also increase the Carbon Dioxide generation by microorganism after 45 days. From FTIR spectrum displayed after 360 days of degradation, the intensity of the peaks significantly decreased and broadens at peak 3302, 1462, 1261, and 1020 cm⁻¹ due to OH and C-O bend as a result from degradation of SS by microorganism. Morphological structure of Hybrid BF was viewed using SEM shown that after 360 days of degradation, there was a lot of detachment of SS from LLDPE matrix as degradation has taken place in the blend films. Hybrid BF A which has 20% of SS exhibits only 3 % of CO₂ generation compare to Hybrid BF E which contain 60% of SS display more active decomposition activity of 12 % CO₂ generation. The optimum filler content was found to be 60% (Hybrid E) which drop in mechanical properties showing high degradability occurred. This is a useful formulation for bio degradable polybag bags and agricultural mulch application.

ACKNOWLEDGEMENT

Firstly, and foremost, I am very grateful to the Minister of Science and Technology (MOSTI) for providing the financial support and Minister of Education (MOE) who had sponsored my scholarship to carry this research work.

Secondly, I would like to express my deepest gratitude and appreciation to my supervisor, Prof. Madya Dr Rahmah Mohamed for her information, invaluable guidance, advices and ideas regarding this project. Her interest and dedication was a core to this project from the beginning until submission of the last element.

I also would like to thank all lecturers who were involved as members of this project especially Prof. Madya Dr Siti Zaleha Sa'ad who complement my work in the same area. Other than that, I would like to extend my sincere gratitude to my beloved father Ab Aziz bin Yahya, my beloved mother Maznah binti Mat Yaacob, my beloved wife Noorasilah binti Humumiri and my beloved daughter Nur Damia Uzma binti Mohd Farhan for their support, understanding and had motivated me in completing this thesis.

Finally, my thankful goes to all my friends, laboratory assistants of the Faculty of Applied Science and also those who contributed directly and indirectly towards my thesis project for their help, guidance and comments.

TABLE OF CONTENTS

	Page
CONFIRMATION BY PANEL OF EXAMINERS	ii
AUTHOR'S DECLARATION	iii
ABSTRACT	iv
ACKNOWLEDGEMENT	v
TABLE OF CONTENTS	vi
LIST OF TABLES	viii
LIST OF FIGURES	ix
LIST OF ABBREVIATIONS	xi
CHAPTER ONE: INTRODUCTION	
1.1 Background of Study	1
1.2 Problems Statement	4
1.3 Significance of study	5
1.4 Objectives of study	6
1.5 Scope and Limitation	6
1.6 Conceptual Frameworks	7
1.7 Hypotheses	7
CHAPTER TWO: LITERATURE REVIEW	
2.1 Material	
2.1.1 Sago Starch (SS)	9
2.1.2 Polyvinyl alcohol (PVOH)	14
2.1.3 Linear Low Density Polyethylene (LLDPE)	16
2.1.4 Glycerol	17
2.1.5 Carbon black	21
2.2 Biodegradability	22
2.2.1 Biodegradable Polymer	24
2.2.2 Mechanism of Biodegradation	29
2.2.3 Factors Affecting Biodegradability	30

2.3	Plastic Waste Problems	30
2.4	Biodegradable Starch Based Film	37
CHAPTER THREE: METHODOLOGY		
3.1	Material	44
3.2	Sample Compounding and Preparation	44
3.2.1	Hybrid Master Batch (MB) Blends Preparation	44
3.2.2	Hybrid Blend Films (BF) Preparation	47
3.3	Testing	48
3.3.1	Tensile Strength Test	48
3.3.2	Water Absorption Test	49
3.3.3	Differential Scanning Calorimetry (DSC)	50
3.3.4	Soil Burial Test	50
3.3.5	Fourier Transform Infra-Red Spectroscopy (FTIR)	52
3.3.6	Scanning Electron Microscopy (SEM)	52
3.3.7	Carbon Dioxide Measurement	53
CHAPTER FOUR: RESULTS AND DISCUSSION		
4.1	Hybrid Masterbatch Blends (MB)	55
4.1.1	Tensile Strength Test of Hybrid MB	55
4.1.2	Water Absorption Test	61
4.1.3	Thermal Behavior Analysis	64
4.1.4	Soil Burial Test of Hybrid MB	67
4.2	Hybrid Blend Films (BF)	70
4.2.1	Soil Burial Test for Hybrid BF	70
4.2.2	Fourier Transform Infra Red (FTIR) of Hybrid BF	72
4.2.3	Scanning Electron Microscopy of Hybrid BF	74
4.2.4	Carbon Dioxide Measurement of Hybrid BF	77
CHAPTER FIVE: CONCLUSION		81
REFERENCES		84
APPENDICES		98
AUTHOR'S PROFILE		101