



**IMPACT PERFORMANCE OF GLASS FIBRE/EPOXY COMPOSITE
MATERIAL**

AHMAD SHARIFUDDIN BIN DAUD @ YUSOF

(99385344)

A thesis submitted in partial fulfillment of the requirements for the award
of Bachelor Engineering (Hons.) (Mechanical)

**Faculty of Mechanical Engineering
Universiti Teknologi MARA (UiTM)**

OCTOBER 2002

ACKNOWLEDGEMENTS

BISMILLAHIRRAHMANIRRAHIM...

In the name of Allah, the most Gracious and most Merciful. All the praises and thanks only to him. We are very grateful for Him as we were given the courage to finish this final project.

First of all, we would like to convey our gratitude and thank to our project advisor, En. Yakub Bin Md. Taib for his guidance, supervision, encouragement and discussion throughout the work on this project. Thank you also to Workshop Technician En. Ab Halim Hussin and En. Mohd Jais Minar, Strength Of Materials Lab Technician; En. Abu Kassim, Metallurgy Lab Technician; En. Hayub and En Mahusin, for their help and advice during preparing samples and conducting tests at Mechanical Engineering Laboratory,

Last but not least, thank you to our classmates for their encouragement throughout this year. Thank you and appreciation to all mentioned above and any other parties, which involved directly or indirectly in preparation of this project. May Allah bless you all for the efforts and help into making this project a success.

ABSTRACT

This project is aimed to study the performance of composite material due to tensile and impact loads. Correlation between the residual tensile strength and the impact energy can then be made. From this, a correlation between damage strength is established.

Damage tolerance of impacted Fibre Reinforced Composites is also an important consideration for the use of the materials particularly in aircraft and automotive industries. In damage tolerance testing, the test piece is subjected to low-blow impact energy levels that do not allow the striker to penetrate the test specimens prior to residual tensile strength evaluation.

From the experimental results, it was found that the material used has three number of layers arranged the following arrangement, [chopped strand/woven/chopped strand]. This arrangement gives tensile strength of 63.46 MPa and maximum impact toughness of about 14.8 Joules fully penetrated.

Microscopic examinations confirm the stacking sequence and type of fibre (chopped strand and plain woven) used. Also from the microscopic the dominant damage/failure mechanism can be ascertained. For non-impact specimen, fracture surface occupied over entire specimen width, whereas for low-impact specimen, damage seems to be localised at a small region.

TABLE OF CONTENTS

CONTENTS	PAGE
ACKNOWLEDGEMENTS	i
ABSTRACT	ii
TABLE OF CONTENTS	iii
CHAPTER I	
GENERAL INTRODUCTION	
1.0 Introduction	1
1.1 Introduction to Composite Material	2
1.1.1 Definition of Composite	2
1.1.2 General Characteristics	4
1.1.3 Production of Glass Fibres	5
1.1.4 Fibreglass Reinforcements for Plastics	6
1.1.5 Fibreglass Reinforcing Mats	6
1.2 Material Study	8
1.2.1 Introduction	8
1.2.2 Glass Fibres for Reinforcing Plastic Resins	8
CHAPTER II	
EXPERIMENTAL STUDIES	
2.0 Introduction	9
2.1 Sample weight ratio & fibre arrangement	12
2.1.1 Theory of Weight Ratio Test	12

2.1.2	Procedure	13
2.2	Tensile Test	14
2.2.1	Theory of Tensile Test	14
2.2.2	Tensile Test Machine	15
2.2.3	Specimen Preparation	15
2.2.4	Tensile Test Procedures	16
2.3	Impact Test	18
2.3.1	Theory of Impact Test	18
2.3.2	Impact Test Machine	19
2.3.3	Specimen Preparation	20
2.3.4	Impact Test Procedures	20
2.4	Microstructure observation	22
2.4.1	Introduction	22
2.4.2	Preparation for microstructure analysis	23
2.4.3	Procedures	24

CHAPTER III

RESULT OF EXPERIMENTAL STUDIES

3.0	Introduction	25
3.1	Result of Microstructure Study	25
3.2	Result of Tensile Test	26
3.2.1	The Result Taken During Experiment	26
3.2.2	Phenomenon of Tensile Test	28
3.3	Result of Impact Test	30
3.3.1	The Result Taken During Experiment	30
3.4	Microstructure Observation	32

CHAPTER IV

DISCUSSION OF EXPERIMENTAL STUDIES

4.0	Introduction	33
4.1	Discussion on Weight Fraction	33