



**CONSTANT LOAD EFFECT ON FRACTURE OF POLYMER CONCRETE (PC)
DUE TO ENVIRONMENT**

**ALIA BINTI IBRAHIM
(2001499525)**

A thesis submitted in partial fulfilment of the requirements for the award
of Bachelor Engineering (Hons) (Mechanical)

**Faculty of Mechanical Engineering
Universiti Teknologi MARA (UiTM)**

APRIL 2005

ACKNOWLEDGEMENTS



In the name of Allah S.W.T, The Most Gracious who has given me strength and ability to complete this project. All perfect praises belong to Allah S.W.T, Lord of Universe. May His blessing upon the Prophet Muhammad S.A.W and members of the family and companions. First of all, I would like to convey my gratitude and thank to my project advisor, En. Yakub Bin Md Taib for his guidance, supervision, encouragement and discussion throughout the work on this project. Thank you also to Workshop Technician; En. Ahmad Kuzairy Omar Bakhi, Strength of Materials Lab Technician; En. Ziyadi Zamri and Metallurgy Lab Technician; En. Hayub Ta and En. Ahmad Hairi Simon for their generous help during preparing samples and conducting tests at Mechanical Engineering Laboratory. Finally to all parties which involved directly or indirectly for their cooperation and encouragement in completion of this research. Thank you.

ABSTRACT

The behavior of compact tension (CT) polymer concrete (PC) when exposed to air, water (pH=7) and sulfuric acid (pH=4) were investigated over a period of one and three weeks, respectively. In this study, CT specimen exposed to air will be considered as optimum condition. Also the effect of environment to PC on the fracture toughness was studied. The decrease in fracture toughness was dependent on the type, concentration and pH of the corrosive solutions. In water and sulfuric acid exposure, PC did show reduced the fracture toughness compared to optimum specimen. Water was the most corrosive media compared to others as it reduced about 15.71% of the fracture toughness. The reduced fracture toughness corresponded to the increasing in pH value. There was linear correlation between the fracture toughness and stiffness. The highest fracture toughness was air at $1.89\text{MPa}\sqrt{\text{m}}$ having stiffness 0.3875kN/mm while the lowest fracture toughness was three weeks immersed in water at $1.59\text{MPa}\sqrt{\text{m}}$ having stiffness 0.3000kN/mm . A fixture was fabricated to conduct constant load test at 90%, 80% and 70% of fracture toughness. PC immersed in sulfuric acid for a week and three weeks show increasing percentage of life time to failure due to fracture at all loading rate. For 80% of fracture toughness loading, there was slightly different in large decreasing percentage of life time to failure for PC immersed in a week (94.95%) compared to three weeks immersed in water (86.77%). The reduced of percentage life time corresponded to suddenly increase uptake of water for the first week immersed. From the observation, decreasing life time to failure due to fracture for PC in all condition had no correlation with increasing load conducted for constant load test.

TABLE OF CONTENTS

CONTENTS	PAGE
PAGE TITLE	i
ACKNOWLEDGEMENT	ii
ABSTRACT	iii
TABLE OF CONTENTS	iv
LIST OF TABLES	vii
LIST OF FIGURES	viii
CHAPTER 1 INTRODUCTION	
1.0 Introduction	1
1.1 Research Background and Problem	2
1.2 Research Requirements	3
1.3 Potential Benefits of the Research Study	3
CHAPTER 2 LITERATURE REVIEW	
2.0 Background of Polymer Concrete (PC)	5
2.1 Introduction to Materials	6
2.1.1 Filler	
2.1.2 Resin	
2.1.2.1 Mechanical Properties of the Resin System	6

2.1.2.2	Adhesive Properties of the Resin	7
2.1.2.3	Toughness Properties of The Resin	7
2.1.2.4	Environment Properties of the Resin	7
2.1.3	Aggregate	9
2.1.4	Coupling	9
2.2	Background of Polyester Polymer Concrete	10
2.3	Concepts and Analysis of Failure	10
2.3.1	Energy Concept of Fracture	11
2.3.1.1	Griffith Theory of Brittle Fracture	11
2.3.2	Fracture Toughness	14
2.4	Some Research by Others	16

CHAPTER 3 RESEARCH METHODOLOGY

3.0	Research Methodology	18
3.1	Preparation of Specimen	19
3.2	Bonding Strain Gage	20
3.3	Fixture Preparation	20
3.4	Fracture Toughness Test	21
3.4.1	Introduction to Fracture Toughness Test	21
3.4.2	Theory of Fracture Toughness Test	21
3.4.3	Fracture Toughness Test Procedure	23
3.5	Constant Load Test	23
3.5.1	Introduction of Constant Load Test	23
3.5.2	Constant Load Test Procedure	23
3.6	Microstructure Observation	24