LIGNOCELLULOSIC THERMOPLASTIC COMPOSITE FROM SHREDDED WASTE PAPER

By

BASHIRAH MOHD SURUR

Thesis Submitted in Partial Fulfilment of the Requirement of the Bachelor of Science (Hons) in Furniture Technology in the Faculty of Applied Science, Universiti Teknologi MARA

October 1999

ACKNOWLEDGEMENTS

I wish to express my gratitude to my supervisors, Dr. Jamaludin Kasim and Mssr. Chen Fung Woo for guiding, reading and offering comments as the thesis evolved. I gratefully acknowledge their helpful suggestion.

I would also like to thank all lecturers and lab assistants in the Department of Furniture Technology, Universiti Teknologi MARA especially to Mssr. Roslan Ali, as Head of Department for guiding me either direct or indirectly. I am very grateful to Mssr. Nawawi Abd Rahman, Head of Department Rubber and Plastic Technology, Universiti Teknologi MARA for permitting me to use the Rubber and Plastic Technology equipment and providing the materials. Also to lab assistance, Mssr. Ismail Ramli and Mustapha Baba for helping me during the thermoplastic making and testing. I wish to pay special tribute to Mssr. Ariff Mohamed whose willingness to contribute his knowledge, time and effort till I completed my thesis. Not forgetting, thanks to all my friends and classmate, for helping me throughout the years.

Finally, my profoundest gratitude goes out to my beloved family, especially to my parents: Hj. Mohd Surur Hj. Mohd Ghazali and

my siblings: Bisyaarah, Nadzirah, Mohd Ghazali, Mohd Ehsan and Mohd Nadzir who had always support me throughout my life.

Thank You.

LIGNOCELLULOSIC THERMOPLASTIC COMPOSITE FROM SHREDDED WASTE PAPER

By

BASHIRAH BINTI MOHD SURUR

October 1999

Shredded waste paper is one of the abundant sources of used fiber. It has the potential to be use as reinforcing fillers in thermoplastic composite. In this experiment the waste paper thermoplastic composite was made through melt-blending process and its physical and mechanical properties were determined. The waste paper and polypropylene (PP) were blended in a dispersion mixer machine and then made into a composite using a mould, with waste paper percentage varying from 0 to 30%. The maleic anhydride grafted polypropylene (MAPP) was added to improve the bonding and interaction between the hydrophilic waste paper and hydrophobic polymer matrix. Composites produced were tested for tensile, flexural and water absorption properties. Results were compared to composite made from 100% neat PP. For thermoplastic composite without MAPP, loading of waste paper into the composite decrease the tensile strength and its ability to elongate. The higher amount of waste paper however increase the modulus of elasticity, water absorption and the flexural strength. addition of MAPP in thermoplastic composite helps to improved the properties of composite. The flexural and tensile strength increases with the addition of MAPP. Overall, the waste paper was found to be a suitable material to be use in the manufacture of thermoplastic composite.

TABLE OF CONTENTS

		Page
ACKN	NOWLEDGEMENTS	ili
	OF TABLES.	٧i
-	OF FIGURES.	v; vii
	OF PLATES	viii
	OF ABBREVIATIONS	ix
	RACT	X
	RAK	хi
CHAF	PTFR	
0 1174		
i	INTRODUCTION	1
()	LITERATURE REVIEW	4
	Paper	4
	Introduction to Paper.	-
	General Grades of Paper	
	Specific Types of Paper	6
	Recycle Paper and Its Disadvantages	
	Composite	
	Thermoplastic Composite	10
	Lignocellulosic Thermoplastic Composite Potential Uses for Lignocellulosic Thermoplastic	. 11
	Composite	12
	Polypropylene as a Binder	13
	Maleic Anhydride Grafted Polypropylene (MAPP)	16
m	MATERIALS AND METHODS	18
	Materials	18
	Methods	
	Thermoplastic Composite Making	19
	Specimen Preparation and Testing	
	Determination of Flexural Strength	
	Determination of Tensile Strength	
	Determination of Water Absorption	33
	Statistical Analysis	35

CHAPTER I

INTRODUCTION

Paper is one of the main product produce from wood or other cellulose fiber material (Biermann, 1993). Most of the fiber sources were from tree. With the felling of so many trees in such a short time, by the year 2000, the timber resources will be running out. Action must be taken to ensure the wood fiber is still available when needed. But how can get more wood fiber without felling more trees?

The world most famous answer to that question is 'recycle" back the paper. Paper is one of the large solid waste producers in the wood-based industry (Franklin, 1974). For the year 1999 from January until May, Malaysia import about RM 179 million worth of writing paper (Anon., 1999). Most of the white paper is used in the office whether for photocopying, faxing, writing and printing documents. After used, often it is discard in shredding machine and thrown in the dump side.

It is such a waste to throw away the waste paper just like that despite the facts that it can be used again. For years, paper mills are trying to