# THE MECHANICAL PROPERTIES OF DIMENSION STABILITY OF KEDONDONG KERANTAI LICHIN (Santiria laevigata)

By

# CHRISTIANUS SAMUIN LOKMAN BIN MOHAMAD

## DIPLOMA IN WOOD INDUSTRY UNIVERSITI TEKNOLOGI MARA, PAHANG

**APRIL 2011** 

### ACKNOWLEDGEMENT

Firstly, we would like thanks to God for giving the good health of body to us in completed and submitted our final year project entitled "The Mechanical Properties of Dimension Stability of kedondong kerantai lichin". I would also like to express my deepest appreciation to my advisor, Miss Zaimatul Aqmar Abdullah for her encouragement and guidance in designing and implementing this project until the end of our study.

Heartiest gratitude we also give to Dr. Wan Mohd Nazri bin Wan Abdul Rahman for his help, support and guidance throughout the course of our study. Not forgetting, thanks are also dedicated to those who were involved directly or indirectly in the completion of this study.

Finally, we would like to apologize if we have committed on offense to all parties, weather involved or not involved in the work of this project. May God blessed and give mercy on us all.

Thank you very much.

### TABLE OF CONTENTS

### CONTENTS

### PAGE

APPROVAL SHEET ii	
ACKNOWLEDGMENTiii	
TABLE OF CONTENTS iv -	v
LIST OF TABLES vi	
LIST OF PLATES vii	
LIST OF FIGURE vii	
ABSTRACT ix	
ABSTRAK x	

### CHAPTER

I.	INTRODUCTION	1 - 2
	<ul><li>1.1 General background</li><li>1.2 Objective</li><li>1.3 Justification</li></ul>	3
II.	LITERATURE REVIEW	5
	2.1 General Descriptions of Kedondong Kerantai Lichin	5
	2.2 General Characteristics	
	2.3 Properties and Density of Kedondong Kerantai Lichin	7 - 8
	2.4 Natural Durability	
	2.5 Defects	
	2.6 Shrinkage	
	2.7 Kiln Schedule.	
	2.8 Machining Properties	
	2.9 Uses	13
III.	MATERIAL AND METHODS	14
	3.1 Raw Material	14
	3.2 Experimental Parameters	
	3.2.1 Temperature	15

	3.4 Material and Methodology	17 - 19
IV.	RESULT AND DISCUSSION	20
	<ul> <li>4.1 Introduction.</li> <li>4.2 Temperature 25°C (Sample A)</li> <li>4.3 Temperature 50°C (Sample B)</li> <li>4.4 Temperature 75°C (Sample C)</li> <li>4.5 Temperature 105 °C (Sample D)</li> <li>4.6 Temperature 105°C (Sample E) Control Sample (72 Hours)</li> <li>4.7 Average of weight loss, length, width and thickness of the sample</li> </ul>	20 20 - 21 22 - 23 23 - 24 25 - 26 26 - 27 28 - 30
v.	CONCLUSION	31
VI.	REFERENCES	32
VII.	APPENDICES	33 - 36
VIII.	CURRICULUM VITAE	37 - 38

## THE MECHANICAL PROPERTIES OF DIMENSION STABILITY OF KEDONDONG KERANTAI LICHIN (Santiria laevigata)

By

## CHRISTIANUS SAMUIN LOKMAN BIN MOHAMAD

### **APRIL 2011**

#### ABSTRACT

This thesis was carried to determine the mechanical properties of dimension stability of kedondong kerantai lichin. The main objectives of this thesis to determine the mechanical properties of dimension stability of kedondong kerantai lichin and determine it drying defect. The initial weight, length, width and thickness and also final measurement of kedondong kerantai lichin has been taken to get the percentage of moisture loss and dimensional changes. For this study four difference temperatures (sample A is 25°C, sample B is 50°C, sample C is 75°C, sample D and sample E (control) are 105°C) with six replicates was prepared. All results of the samples showed decreasing in the final weight, length, width and thickness. The drying defects that appear in all sample of kedondong kerantai lichin are crack.