

**ANATOMICAL PROPERTIES OF PULAI**  
**(*Alstonia angustiloba*)**

By

**Noor Khafiz Ramli**

**Final Project Paper Submitted in Partial Fulfillment for the Diploma in Wood  
Industries, Faculty of Applied Science,  
Universiti Teknologi MARA**

**October 2000**

## **ACKNOWLEDGEMENT**

In the name of Allah S.W.T., I wish to my express my deepest appreciation and sincere thanks to my advisor Assoc. Prof. Dr. Suhaimi Mohammed for his guidance, suggestion, advises and constructive, critic through the preparation of this project paper.

My sincere appreciation also goes to Assoc. Prof. Dr. Jamaludin Kasim as Course Tutor and lecturer of WTE 375 for allowing using the facilities of faculty to carry my experimental works and the laboratory assistant, Mr. Rudaini Mohd. Nawawi, for his valuable help and co-operation.

Finally, special thank to all my beloved friends and classmate also to those who are involved either directly or indirectly for their help and moral support during the whole period of this project.

## TABLE OF CONTENTS

	<b>Page</b>
<b>ACKNOWLEDGEMENTS</b>	iv
<b>LIST OF FIGURES</b>	vii
<b>LIST OF PLATES</b>	viii
<b>ABSTRACT</b>	ix
<b>ABSTRAK</b>	x

### CHAPTER

<b>1</b>	<b>INTRODUCTION</b>	<b>1</b>
	1.1 Overview	1
	1.2 Objectives	2
<b>2</b>	<b>LITERATURE REVIEW</b>	<b>3</b>
	2.1 Anatomical Properties of Wood	3
	2.1.1 Vessel and Pores	4
	2.1.2 Wood Parenchyma	5
	2.1.3 Rays	7
	2.1.4 Fibers	7
	2.1.5 Tyloses	8
	2.1.6 Included Phloem	8
	2.1.7 Intercellular Canals	8
	2.2 Heartwood and Sapwood	8
<b>3</b>	<b>MATERIALS AND METHODS</b>	<b>10</b>
	3.1 Preparation of Materials	10
	3.1.1 Wood Block Slicing	15
	3.1.2 Wood Block Selection	15
	3.1.3 Cutting Angel	15
	3.2 Sectioning	15
	3.3 Staining and Mounting	16
	3.4 Scanning Microscope of Wood Specimens	17
<b>4</b>	<b>RESULTS AND DISCISSIONS</b>	<b>19</b>
	4.1 Transverse Section	19
	4.2 Tangential Section	21

4.3 Radial Section	23
<b>5 CONCLUSIONS</b>	<b>25</b>
<b>REFERENCES</b>	<b>26</b>
<b>VITA</b>	<b>27</b>

## **Abstract**

### **ANATOMICAL PROPERTIES OF PULAI (*Alstonia angustiloba*)**

By

**NOOR KHAFIZ RAMLI**

October 2000

Anatomical properties of Pulai (*Alstonia angustiloba*) based on DBH portion of the tree were studied. The tree was obtained from UiTM Pahang Forest Reserve. The nature of pores or vessels is mainly radial multiple of three up to seven in number. Few solitary pores were present, moderate to large size pores. The natures of wood rays are of two types namely multiseriate and uniseriate. The former types of rays are more predominant. This information is fundamental which could assist in proper wood utilization.