# SOME SELECTED PROPERTIES OF POLYPROPYLENE COMPOSITE USING LUDAI PARTICLES AS FILLERS

By

Noraini Binti Mohamad

Final Project Submitted in Partial Fulfillment for the Diploma in Wood Industries, Faculty of Applied Science, University of MARA Technology

September 2002

#### ACKNOWLEDGEMENTS

First of all, I would like to thank ALLAH S.W.T for His blessing and strength rendered to enable me to complete my final project.

I would also like to offer my special thanks to my project advisor Prof. Madya Dr. Jamaludin bin Kasim for his guidance and patience in helping me at every phase of the study. Deepest appreciation is also extended to my lecturers especially En Wan Mohd Nazri bin Wan Abdul Rahman and En.Amaran bin Shafie for their commitment during my research. I also wish thank to En.Ismail and En.Anuar for giving full co-operation during my research in laboratory at the School Applied Science, UiTM Shah Alam.

I also wish to thank all my friends who in one way or another contributed invaluable support and encouragement towards the completion of this study.

Finally, my deepest and special appreciation goes to my beloved parents for their moral and financial support throughout the years of my study. May Allah S.W.T bless all of you.

iv

### **Table of Contents**

# Page

5

APPROVAL SHEETS	ii
DEDICATION	iii
ACKNOWLEDGEMENTS	iv
LIST OF TABLES.	vii
LIST OF FIGURES.	viii
LIST OF PLATES	ix
LIST OF ABBREVIATION.	x
ABSTRACT	xi
ABSTRAK	xii

CHAPTER I	
1.0 Introduction	1
1.1 Problem Statement	2
1.2 Objective.	2

## **CHAPTER II**

2.0 Literature Review	3
2.1 Ludai (Sapium bacattum)	3
2.2 Composite	3
2.3 Polypropylene	4
2.4 Lignocellulosic Composite	5
2.5 Potential of Lignocellulosic Thermoplastic Composite	6

## CHAPTER III

3.0 Material and Method	8
3.1 Material Preparations	8
3.2 Blending Ludai Particles and Polypropylene	10
3.3 Composite Manufacture	13
3.4 Composite Testing	16
3.4.1 Bending Test	16
3.4.2 Tensile Testing	18
3.4.3 Water Absorption	22

CHAPTER IV	
4.0 Result and Discussion	23
4.1 Physical and Mechanical Properties	23
4.2 Effects of Filler Loading	24

# LIST OF PLATE

Plate		Page
1	The use of lignocellulosic as reinforcing fillers allows thermoplastic to be molded into a wide variety of shapes (www.msn.com)	7
2	Dispersion Mixer	10
3	Crusher Machine	11
4	Bending Sample (30 g) mould	13
5	Bending Sample after Hot Pressing	14
6	Tensile and Water Absorption after Hot Pressing	14
7	Hot Press	15
8	Cold Press Machine	16
9	Bending Test	17
10	Tensile Test	20

#### ABSTRACT

### SOME SELECTED PROPERTIES OF POLYPROPHYLENE COMPOSITE USING LUDAI PARTICLES AS FILLER

By

#### NORAINI BINTI MOHAMAD

September 2002

In this study thermoplastic composite was produced from particles of Ludai (*Sapium baccuttum*) mixed with polypropylene (PP). The filler-loading ratio used in the study was 10%, 30%, and 50%. Physical and mechanical tests such as thickness swelling, water absorption, flexural and tensile strength, elongation at break and elasticity modulus were carried to determine the effects of filler loading. The results show that thickness swelling (TS) and water absorption (WA) decreased with higher filler loading. The mechanical properties of flexural, tensile strength and elongation at break decreases significantly with higher filler while flexural and tensile modulus increases. Ludai particles are suitable to be used as fillers in the manufacture of Polypropylene-composite.