# DENSITY AND SPECIFIC GRAVITY OF GERONGGANG (Crotoxylum spp) ACCORDING TO DIFFERENT HEIGHT LEVELS

BY

### **ROSZANA BINTI DERANI**

Final Project Submitted in Partial Fulfillment for the Diploma in Wood Technology, Faculty of Applied Science, Universiti Teknologi MARA, Pahang Branch October 2004

### ACKNOWLEDGEMENT

Alhamdulillah, praise is to Allah, the almighty for giving me strength and opportunity to complete this project.

I would like to express my deepest appreciation and since gratitude to my advisor, Encik Ahmad Fauzi Bin Othman for his valuable assistance and guidance. He has help me in many ways by providing information, teaching me the correct method and helping me in every way that ha can order for me to complete my task. To my tutorial lecture Prof. Abdul Jalil Bin Ahmad that also give me more knowledge to complete this project paper. Special thanks also to my entire lecturer in Diploma In Wood Indutry (DIP) for your helping for give me some information.

Special thanks to my beloved family that also give me support, strength and advice to keep up with the study and constantly encouraging me towards the success of this final project.

Lastly, thanks you to all my friends and those who are involved either directly or indirectly in completing this project. And for someone special that also give advice for me from first me study in this course until today Puan Shahlawati Bt Mohammed Sah that also give me support and advice everyday when I at here. Thank you so much for you. May Allah bless us in our end devour.

# **TABLE OF CONTENTS**

### PAGE

1

2

3

APPROVAL SHEET	i
DEDICATION	ii
ACKNOWLADGEMENT	iii
LIST OF TABLES	v
LIST OF FIGURES	vi
LIST OF ABBREVIATION	
ABSTRACT	viii
ABSTRAK	

## CHAPTER

1.0 INTRODUCTION
1.1 Introduction of Density and Specific Gravity
1.2 Objectives
2.0 LITERATURE REVIEW
2.1 General Characteristic of Geronggang
2.2 Physical Properties of Geronggang

66 6	
2.2 Physical Properties of Geronggang	4
2.3 Mechanical Properties of Geronggang	4
2.4 Uses	5
2.5 Importance of Density and Specific Gravity	5

## **3.0 MATERIAL AND METHODS**

3.1 Preparation of Raw Material	6
3.2 Density and Specific Gravity Measurement	
3.2.1 Procedure of Density Determination	
3.2.2 Procedure of specific Gravity Determination	9

## 4.0 RESULTS AND DISCUSSION

4.1 The Effect of Geronggang Density	
4.2 The Effect of Geronggang specific Gravity	14
5.0 CONCLUSION	16
REFERENCES	17
APPENDICES	18
VITA	31

# LIST OF TABLES

# PAGE

1.	The result of density according height level	11
2.	The result of specific gravity according height level	13
3.	Mean result of density and specific gravity	17
4.	Raw data of density on Top, Middle and Base	18-23
5.	Raw data of specific gravity on Top, Middle and Base	24-29

### DENSITY AND SPECIFIC GRAVITY OF GERONGGANG (Crotoxylum spp)

### **ACCORDING TO DIFFERENT HEIGHT LEVELS**

By

#### ROSZANA BT DERANI

#### October 2004

### ABSTRACT

The study of density and specific gravity was performed on Geronggang wood *(crotoxylum spp).* Specific gravity was determined using the maximum moisture content method and density is known as plugs per cubic meter. From the samples were analyzed from the different height level- top, middle and DBH (base). The result indicated that the density was highest at base and lowest at the middle level. On the other hand, specific gravity decreased from the base portion until then to the top portion. Thus specific gravity is inversely related to different height levels.