PROPERTIES OF PARTICLEBOARD 450Kg/m³ FROM SESENDUK (Endospermum Malaccensis)

By NORJIHAN BINTI A. BAKAR

Final project submitted in partial fulfillment for the Diploma in Wood Industries, Faculty of Applied Sciences, Universiti Teknologi MARA, Pahang

April 2005

ACKNOWLEDGEMENT



Assalammualaikum

I would like to take this opportunity to express our special thanks to Allah S.W.T for his blessing and strength rendered to me completed my thesis project which the title is about particleboard and I would like to offer the special thanks to our beloved parents who always give me moral, good advices and support to be as a good and responsibility student.

Sincere thanks are due to Mr. Ahmad Fauzi bin Othman, who is advisor for this project because he was teaching and help me as practically about this project, so that I can get more experience and completely knowledge in making process of particleboard. Beside that thank you to Prof. Madya Dr. Jamaluddin Bin Kassim, Amran Bin Safiee and Shaikh Abdul Karim Yamani for their encouragement, helping and guidance in this study. Also, special thanks to Mr. Sardey who is assistant of woodtech factory because his extending all facilities and cooperation given during this study.

TABLE OF CONTENT

Titles		Pages
DEDICATIONACKNOWLEDGEN LIST OF TABLES LIST OF FIGURES LIST OF PLATES LISTS OF ABBREY ABSTRACT	TIATIONS.	ii iii iv-v vi vii viii ix x
CHAPTER I		
1.1 General characteristics 1.2 Justification	nn	1 1-4 5 6
20 LITERATURE R	EVIEW	7
2.1 Particleboard world industry		7-8
2.2 Status industry particleboard in Malaysia		9-11
2.3 Uses		11
2.4 History of particleboard		12-15
2.5 Wood wastes		16
	Vernacular names	16
2.5.2	Distribution and Growth attributes	16
2.5.3	General characteristic.	17
2.5.4	General properties.	18-19
2.5.5	Morphology	19-20
2.5.6	Wood anatomy	20-21
2.5.7	Ecology	21
2.5.8	Harvesting	22
2.5.9	Prospect	23
2.5.10	Uses	23-25

2.6 Urea Formaldehyde resin		
2.8 Effect of Resin.	28	
CHAPTER III		
3.0 MATERIAL AND METHODOLOGY	29	
3.1 Material preparation for particleboard	29	
3.1.1 Wood	29	
3.1.2 Glue (UF)	30	
3.1.3 Hardener	30	
3.1.4 Wax	30	
3.2 Preparation of specific gravity		
3.3 Preparation of particles geometry	34	
3.3.1 Particles classification	34	
3.3.2 Flakes thickness and length of particles	35	
3.4 Bulk density	36	
3.5 Particleboard manufacturing explanation	37-49	
3.6 Type of testing.	50	
3.6.1 Mechanical testing	50-52	
3.6.2 Physical testing.	53-54	
3.7 Treatment	55	
CHAPTER IV		
4.0 RESULT AND DISCUSSION	56	
4.1 Mechanical testing.	58-63	
4.2 Physical testing.	64-66	
CHAPTER V		
5.0 CONCLUSION AND RECOMMENDATION		
DEFEDENCES	(0.70	
REFERENCES	69-70	

PROPERTIES OF PARTICLEBOARD 450 kg/m³ FROM SESENDUK (*Endospermum Malaccensis*)

By

NORJIHAN BINTI A. BAKAR

APRIL 2005

ABSTRACT

Particleboard is one of many wood composites. Today, this panel is the most popular in furniture industry since this tremendous material replace plywood for building construction and furniture industry. In this study the *Endospermum malaccessis* selected as raw material with density 450kg/m³ also three percentage of resin Urea Formaldehyde that is 8%, 10% and 12% are used to make this particleboard. The physical and mechanical properties of this board will determine by several types of test. The result shows that the percentage of resin are used affecting the strength of this board. From this study the physical properties and some bending strength not reach the value of standard that has been specified.