Electrical and Optical Properties of Nanocomposited MEH-PPV: CNTs Organic Solar Cell Thin Film

This thesis is presented in partial of fulfilment for the award of the

MARA in partial fulfilment for the award of Bachelor of Electrical Engineering

Bachelor of Electrical Engineering (Hons)
UNIVERSITI TEKNOLOGI MARA (UITM)
SHAH ALAM, MALAYSIA
(MAY 2011)



MOHD HAZRIN BIN ZAINAL
NANO-ELECTRONIC CENTRE
FALCULTY OF ELECTRICAL ENGINEERING
UNIVERSITI TEKNOLOGI MARA
40450 SHAH ALAM,
MALAYSIA

ACKNOWLEDGEMENT

First and foremost, I would like to thank my supervisor, Madam Zurita Zulkifli and my co-supervisor, Dr. Sukreen Hana Herman for advice, encouragement, guidance and enthusiasm given throughout the progress of this project.

My appreciation also goes to my family who has been tolerant and support all these years. Thanks for the encouragement, love and emotional support that they had given all the time.

I also would like to acknowledge all members of NANO- ElecTronic Centre UiTM Shah Alam, especially to Madam Puteri Sarah for their technical support, guidance and encouragement in this project.

Nevertheless, my great appreciation dedicated to my friend and my entire batch in UiTM Shah Alam, those whom involve directly or indirectly with this project. Your kindness will be remembered until the end of life. Thank you.

Mohd Hazrin Bin Zainal
Faculty of Electrical Engineering
Universiti Teknologi MARA (UiTM)
Shah Alam, Selangor Darul Ehsan
Malaysia

ABSTRACT

This research focused on the electrical and optical properties of nanocomposited MEH-PPV: CNTs organic solar cell thin film with different composition ratio of CNTs. The project are focusing on adding 0 wt%,1 wt%, 2 wt%, 3 wt% and 4 wt% of the CNTs in order to observe the effect on it. The toluene been used as solution to dissolve the MEH-PPV and CNTs. The thin film was deposited on 2cm x 2cm glass substrate by using spin coating technique. The electrical properties characterize been done by using two point probe solar simulator to measured the current-voltage characteristic. The optical properties of the thin film were characterized using UV-VIS/NIR spectrophotometer to observe the absorption and transmittance characteristic. The current-voltage was measure in two condition, which is in dark and illumination condition. The highest value of conductivity among the 5 concentration is at 4wt% concentration of CNTs with 0.02738 Sm⁻¹. The smaller optical band gap among the 5 concentration was recorded at 4wt% concentration of CNTs which is at 2.00eV.

Keywords: MEH-PPV, CNTs, nanocomposited MEHPPV: CNTs, Spin Coating

TABLE OF CONTENT

CONTENT	Acetons	PAGE
Declaration		i ??
Dedication		ii
Acknowledg	gement PARPARATION	iii
Abstract	IN FILM DEPOSITION	iv
Table of Content CHARACTERIZATION		v
List of Figures Physical Characterization		vii
List of Tables Characterization		ix
List of Abbi	reviations	x
CHAPTER	1:INTRODUCTION	
1.1 ORG	GANIC SOLAR CELL	1
1.2 BAC	CKGROUND OF STUDY	3
1.3 PROBLEM STATEMENT		3
1.4 OBJECTIVE OF THE RESEARCH		4
1.5 SCOPE OF STUDY		ANDATION 5
1.6 THE	ESIS OVERVIEW	5
CHAPTER	2:LITERATURE REVIEW	
2.1 POLYMER MEH-PPV		7 7
2.2 CAF	RBON NANOTUBE	9
2.2.1	Special properties of CNT	11
2.2.2	Chemical reactivity	- 11
2.2.3	Electrical conductivity	12
2.2.4	Optical activity	12
2.2.5	Mechanical structure	13
2.3 WEI	IGHT RATIO	13
2.4 SOL-GEL METHOD		14
2.5 THIN FILM		14
2.6 SPIN COATING TEACHNIQUE		15
2.7 ELECTRICAL PROPERTIES		17
2.8 OPT	.8 OPTICAL PROPERTIES	

CHAPTER 1

INTRODUCTION

1.1 ORGANIC SOLAR CELL

An organic solar cell is the cells that use organic compounds as electronic substance. It is also known as a branch of the electronics associated with the organic polymer. Organic solar cells must have a conductive material or a small organic molecule that is used as an absorption component to the light and as the electron conductive. The green technology that been produce while using organic compound. The advantages of the organic material is the low production cost, it can be large scale production and flexibility of organic material. Combination of polymer with the flexibility organic molecules, this makes it potentially lucrative for solar cell application. Molecular engineering like changing the length and functional group of polymer can change the energy gap, which allows chemical change in these materials. The optical absorption coefficient of organic molecules is high so a large amount of light can be absorbed with a small amount of materials. The main disadvantages associated with organic solar cells are the low efficiency, low stability and low strength compared to inorganic solar cells.

Green technology that been developed today is really rapidly grow. The advantages of organic materials is the low production costs, therefore it can be produced with a larger scale and the flexibility of an organic material itself. The combination of polymer with organic molecules would result in term of potentially lucrative an organic substance for the solar cell applications. Organic molecular elasticity and the ability to change form of functional groups will help increase the quality of a solar