

UNIVERSITI TEKNOLOGI MARA

**INVESTIGATION ON ROBOTIC GAS
METAL ARC WELDING QUALITY
FOR SPECIFIC SHIP PANEL
STRUCTURE**

MOHAMMAD RIDZWAN BIN ABDUL RAHIM

Thesis submitted in fulfillment
of the requirements for the degree of
Master of Science

Faculty of Mechanical Engineering

August 2014

AUTHOR'S DECLARATION

I declare that the work in this thesis was carried out in accordance with the regulations of Universiti Teknologi MARA. It is original and is the result of my own work, unless otherwise indicated or acknowledge as referenced work. This thesis has not been submitted to any other academic institution or non-academic institution for any degree or qualification.

I, hereby, acknowledge that I have been supplied with the Academic Rules and Regulation for Post Graduate, Universiti Teknologi MARA, regulating the conduct of my study and research.

Name of student : Mohammad Ridzwan Bin Abdul Rahim

Student I.D. No. : 2010463904

Programme : Master of Science

Faculty : Faculty of Mechanical Engineering

Title : Investigation on Robotic Gas Metal Arc Welding
Quality for Typical Ship Panel

Signature of Student :

Date : August 2014

ABSTRACT

Robotic Welding (RW) is an ideal welding method to produce airtight joint. Many parameters affect the RW quality as welding current, welding voltage, travel speed, width of weaving, torch angle, width plate, clamping position and time gaps between passes. Welding input parameters play a very significant role in determining the quality of a weld formation. This parameter is applied on v-butt joint and t-fillet joint with plate thickness 4mm, 6mm and 9mm. This project is to study the Design of Experiment (DoE) which can approach the optimization of parameter design. Functions for DoE can help to create and test practical plans to gather data for statistical modelling. DoE is a structured, organized method that is used to determine the relationship between the different factor (Xs) affecting a process and the output of process (Y). DoE involves designing a series of experiments, in which all relevant factors are varied systematically. When the results of these experiments are analyzed, they help to identify optimal conditions, the factors that most influence the result, those that do not, as well as details such as the existence of interactions and synergies between factors. The average percentage error for plate thickness 9 mm butt joint by using Fractional Factorial Design is 10.049 %. The optimum parameter would be utilized to develop Welding Procedure Specification (WPS). As the final objective, the development of WPS in this project will be applied to ship panel.

TABLE OF CONTENTS

	Page
AUTHOR'S DECLARATION	ii
ABSTRACT	iii
ACKNOWLEDGEMENT	iv
TABLE OF CONTENTS	v
LIST OF TABLES	ix
LIST OF FIGURES	xiv
LIST OF ABBREVIATIONS	xx
CHAPTER ONE: INTRODUCTION	
1.1 Background of the Study	1
1.2 Problem Statement	2
1.3 Objective of the Research	3
1.4 Scope of the Research	3
1.5 Significant Contribution to New Knowledge	4
CHAPTER TWO: LITERATURE REVIEW AND FUNDAMENTAL THEORY	
2.1 Literature Review	5
2.2 Robotic Welding Process and Welding Parameters	5
2.3 Statistical Evaluation Method by using Design of Experiment (DoE)	7
2.3.1 Taguchi and Multi-Objective Taguchi Method	8
2.3.2 Response Surface Methodology (RSM)	10
2.3.3 Factorial Design	10
2.3.4 Multiple Regression Model	11
2.4 Welding Discontinuity and Defect	12

CHAPTER THREE: METHODOLOGY

3.1	Introduction	17
3.2	Step 1: Literature Review and Workpiece Preparation (Geometries and Equipment)	19
3.3	Step 2: Developing WPS and Optimizing Welding Parameter	22
3.4	Step 3: Investigate on Combination of Butt and T-Joint	23
3.5	Step 4: Investigate on Welding Quality of Ship Panel Structure	23

CHAPTER FOUR: ROBOTIC WELDING APPLICATION FOR SHIP PANEL STRUCTURE

4.1	Preliminary Development of Robotic Welding Parameters	24
4.1.1	Experimental Study on Single-pass Butt and T-Joint for 4mm Plate	25
4.1.2	Experimental Study on Double-pass Butt and T-Joint for Thickness of 6mm	29
4.1.3	Experimental Study on Three-pass Butt and T-Joint for 9mm Plate Thickness	32
4.1.4	Experimental Study on Combined Butt and T-Joint with Thickness of 9mm	36
4.1.5	Result Analysis from Preliminary Experimental Investigation	52
4.2	Welding Procedure Specification (WPS) for Plate with Thickness of 9mm	53
4.2.1	Visual Inspection Report for Butt Joint	55
4.2.1.1	Non-Destructive Test (NDT)	55
4.2.1.1.1	Radiograph Test	55
4.2.1.2	Destructive Test	56
4.2.1.2.1	Bending Test	56
4.2.1.2.2	Macro Etching Test	57
4.2.1.2.3	Hardness Test	58
4.2.1.2.4	Tensile Test	59
4.2.1.2.5	Nick Break Test	60
4.2.1.2.6	Charpy Test	61
4.2.2	Visual Inspection for T-Joint 9mm	63