

UNIVERSITI TEKNOLOGI MARA

**EFFECTS OF HOT-SPOT TEMPERATURE,
MICROSTRUCTURE AND BaAl_2O_4
ADDITION ON OXYGEN SENSING
PROPERTIES OF $\text{REBa}_2\text{Cu}_3\text{O}_{7-\delta}$
(RE=Er, Dy) CERAMIC RODS**

MISBAH BIN HASSAN

**Thesis submitted in fulfillment of the requirements
for the degree of
Doctor of Philosophy**

Faculty of Applied Sciences

March 2012

ABSTRACT

Oxygen sensing properties of REBa₂Cu₃O_{7- δ} -based (RE123, RE = Er and Dy) ceramics utilizing the hot spot phenomenon have been investigated. Although shorter rods of around 12 mm are more practical for industrial use compared to previously reported rods longer than 30 mm, their oxygen sensing properties have not been previously reported. Bulk 123 materials were synthesized using the conventional solid-state method and fabricated into short rods of around 12-mm length with cross sectional area of 0.65 mm \times 0.65 mm. In the first part of this study, influence of hot-spot temperature in the range of 160 °C to 810 °C on oxygen sensing behavior of Er123 rods was studied. Simultaneous measurements of hot-spot temperature and output current response in different oxygen partial pressures between 1 % and 100 % with hot-spots operating at temperatures as low as 660 °C in 1 % oxygen partial pressure produced good sensor current stability as well as repeatability. Response time for oxygen sensing was observed to decrease with increasing hot-spot temperature, with minimum value of 0.50 s recorded at 695 °C in 1 % oxygen partial pressure. In addition, a large change in activation energy of oxygen ion migration from 2.8 eV to 0.626 eV was established at around 670 °C. By using wider Er123 rod, it was demonstrated that hot spot formation starts from local heating at a point of defect before growing in size. In the second part of this study, performance test of the sensor from as low as 0.025 % pO_2 to 100 % pO_2 showed very good repeatability and stability of output current. Electrical conductivity for pO_2 from 5 % to 100 % showed good proportional relation to $pO_2^{1/6}$ and in agreement with the mass action law. In the third part of this study, effect of addition of BaAl₂O₄ on the durability of Er123 rods was studied. It was found that although durability was enhanced, the addition also increased minimum power consumption of Er123 rods. Interestingly, further addition of BaAl₂O₄ from 5 to 30 wt.% has resulted in a reduced minimum power consumption from 1.23 to 1.16 W. Compared to using longer Gd123 rods as reported in a previous study, using Er123 with 30 wt. % BaAl₂O₄ has proven to lower minimum power consumption by at least around 42%. Addition of BaAl₂O₄ also reduced the fluctuation of current and increased the sensitivity for below 10 % pO_2 . In the fourth part of this study, oxygen response of hot spot on Dy123 ceramic rods fabricated under different heat treatments has also been studied. It was observed that increasing the sintering temperature from 900 °C to 960 °C reduced the voltage at peak current by half but only slightly reduced the power consumption. In terms of durability the best performance is shown by the sample which was sintered for 48 hours at around 900 °C. The sample which was reheated at around 910 °C for 24 hours after being fabricated into rod shape showed the largest reduction in voltage at peak current and the lowest in power consumption but it was the least durable. The effect of heat treatment on I-V behavior was discussed in terms of differences in microstructure and initial oxygen content of the samples. These studies have shown that stability of hot-spot based oxygen sensing properties of shorter RE123 rods of around 12 mm in length is influenced by hot-spot temperature, addition of BaAl₂O₄ as well as changes in microstructure as a result of differences in heat treatment. Electrical conductivities of the rods involve oxygen ions and obey the mass action law. At the end of this study, a qualitative model of a special material to control maximum hot-spot temperature based on the temperature at maximum resistivity of the rod material for ceramic rods with hot spot has been proposed.

ACKNOWLEDGEMENT

Alhamdulillah, praise be to Allah, the Most Gracious and Most Merciful for giving all essences and inspiration.

I am very grateful to my supervisor, Prof. Dr. Ahmad Kamal Yahya for his invaluable advice, guidance, help and support during the research period and also to my co-supervisor, Assoc. Prof. Dr. Umi Sarah Jais for her help when needed.

I would like to thank all the people who have helped me, especially to Dr. Z. Awang from Microwave Technology Center, Dr. K. H. Ku Hamid from Faculty of Chemical Engineering, Mr. M. H. Ismail from Faculty of Mechanical Engineering and Ms. J. Karim from Faculty of Applied Sciences for their help in structure and microstructure analyses; all the members in Faculty of Applied Sciences, especially from Superconductor and Advanced Materials Research Group for their help and shares during experimental works; and Dr. T. Okamoto from Department of Electrical Engineering, Nagaoka University of Technology, Japan for his valuable information and discussion leading to this research.

I would also like to thank Malaysian Ministry of Science, Technology and Innovation for E-Science Grant and Malaysian Ministry of Higher Education for FRGS Grant to support this research and Universiti Teknologi MARA for the scholarship scheme.

Most importantly, I would like to give my special thanks to my family for their love, support and understanding, and especially their patience and encouragement for enabling me to finish the study successfully.

TABLE OF CONTENTS

TITLE PAGE	i
AUTHOR'S DECLARATION	ii
ABSTRACT	iii
ACKNOWLEDGEMENT	iv
TABLE OF CONTENTS	v
LIST OF TABLES	ix
LIST OF FIGURES	x
LIST OF PLATES	xiv
LIST OF ABBREVIATIONS	xv
LIST OF PUBLICATIONS	xviii

CHAPTER 1: INTRODUCTION

1.1	Background	1
1.2	Problem statements	4
1.3	Objectives	6
1.4	Significance of study	7

CHAPTER 2: LITERATURE REVIEW

2.1	RE123 compounds	8
2.2	Some properties of Y123	8
2.2.1	Structure of Y123	8
2.2.2	Temperature and oxygen partial pressure dependence of oxygen nonstoichiometry and orthorhombic-tetragonal (O-T) transition	11
2.2.3	Diffusion of oxygen gas in Y123	13
2.2.4	Electrical conductivity mechanism in Y123	14
2.3	Properties of other RE123s and RE ³⁺ ionic radius dependence	16
2.4	Hot spot phenomenon	20
2.5	Oxygen sensor utilizing constant current region	26
2.5.1	Sensitivity	27
2.5.2	Oscillatory current effect	30
2.5.3	Melting due to high temperature of hot spot	31
2.5.4	Minimum power consumption	32
2.6	Oxygen sensing response before constant current region	34

CHAPTER 3: MATERIALS AND METHODS

3.1	Preparation of bulk RE123 samples	36
3.2	Preparation of BaAl ₂ O ₄ added-Er123 samples	37
3.3	Fabrication of sensor rods	37
3.4	Characterization of samples	38
3.4.1	Structure investigation	38
3.4.2	Microstructure and elemental distribution investigation	39
3.5	Resistivity versus temperature measurements	39
3.6	Current-voltage measurements with hot spot	41