

UNIVERSITI TEKNOLOGI MARA

**FABRICATION OF NANO-
COMPOSITED Sn-doped ZnO/TiO₂
BASED DYE-SENSITIZED
SOLAR CELLS**

SAURDI BIN ISHAK

PhD

August 2018

AUTHOR'S DECLARATION

I declare that the work in this thesis was carried out in accordance with the regulations of Universiti Teknologi MARA. This work is original and is the result of my own work, unless otherwise indicated or acknowledged as referenced work. This thesis has not been submitted to any other academic institution or non institution for any other degree of qualification.

I, hereby, acknowledge that I have been supplied with Academic Rules and Regulations for Post Graduate, Universiti Teknologi MARA, regulating the conduct of my study and research. In the event that my thesis be found to violate the conditions mentioned above, I voluntarily waive the right of conferment of my degree and agree be subjected to the disciplinary rules and regulations of Universiti Teknologi MARA.

Name of Student : Saurdi Bin Ishak
Student I.D. No. : 2011268016
Programme : Doctor of Philosophy - EE990
Faculty : Electrical Engineering
Thesis Title : Fabrication of Nano-Composited Sn-doped ZnO/TiO₂
Based Dye-Sensitized Solar Cells

Signature of Student :

Date : August 2018

ABSTRACT

Dye-sensitized solar cells (DSSCs) that belong to the third generation of solar cells are attractive due to cheap and ease of solar cell fabrication. Therefore, much research has been conducted to create an efficient solar cell. The following research illustrates for the first time development of aligned ZnO nanorod on Sn-doped ZnO films by using sonicated sol-gel immersion methods for dye-sensitized solar cells and the fabricated DSSCs show the improvement of photovoltaic properties and than from a novel photoanode of nano-composited aligned ZnO nanorod/TiO₂:Nb a significant improvement on photovoltaic properties was obtained. The Sn-doped ZnO films were used as a seed layer for nanorod growth, where the Sn-doped ZnO films at 2 at.% shows the best of electrical and optical properties. As a result, the aligned ZnO nanorod with relatively high aspect ratio was grown on ITO-coated glass at 2 at.% Sn-doped ZnO films using sonicated sol-gel immersion methods. The resulting of ZnO nanorod length and diameter were around 1.8 μ m and 120nm, respectively. Since the absorption of dye is dependent to aspect ratio or surface area ZnO nanorod and therefore the fabricated DSSCs shows improvement of energy conversion efficiency 0.599% as compared to the fabricated DSSCs using aligned ZnO nanorod on undoped ZnO film, ZnO nanorod on 1 at.% Sn-doped ZnO film and ZnO nanorod on 3 at.% Sn-doped ZnO film were 0.107%, 0.250%, and 0.206%, respectively. Besides that, the surface area of aligned ZnO nanorod was increased by varying the solution concentration parameter. It was found that by using 0.03M Zinc acetate solution the aspect ratio of ZnO nanorod was higher as compared to 0.05M. Therefore, the fabricated DSSCs using 0.03M ZnO nanorod shows the improvement of efficiency to 0.989 %. The aligned ZnO nanorod with better aspect ratio and larger surface area was efficiently for dye absorption and light harvesting that contributed to the improvement of DSSCs. Meanwhile, the presence of TiO₂ nanoparticles on top of ZnO nanorods might increase the internal surface area of photoanode that absorbed more dye molecules and resulting of increasing the photocurrent density 8.579 mA/cm² as well as energy conversion efficiency of 2.543%. Furthermore, the improvement of DSSCs for nano-composited aligned ZnO nanorod/ TiO₂:Nb was closely related to the improvement of electrical properties of TiO₂ nanoparticle from Nb-doped TiO₂ at 5 at.%. The Nb-doped TiO₂ at 5 at.% shows higher of electrical properties that contributes better of electron transport properties. A novel photoanode of nano-composited aligned ZnO nanorod/TiO₂ with Nb-doped TiO₂ at 5.% shows the significant improvement of photocurrent density and energy conversion efficiency of 18.156 mA/cm² and 5.376%, respectively. The enhancement of energy conversion efficiency of the nano-composited aligned ZnO Nanorod/TiO₂:Nb-5 at.% DSSCs can be due to the enhanced electron-injection efficiency caused by the positive shift in V_{fb} which help increase J_{sc} and reduce the charge recombination.

TABLE OF CONTENTS

	Page
CONFIRMATION BY PANEL OF EXAMINERS	ii
AUTHOR'S DECLARATION	iii
ABSTRACT	iv
ACKNOWLEDGEMENT	v
TABLE OF CONTENTS	vi
LIST OF TABLES	xi
LIST OF FIGURES	xii
LIST OF ABBREVIATIONS	xvii
CHAPTER ONE: INTRODUCTION	1
1.1 Introduction	1
1.2 Problem Statement	5
1.3 Objective of the Research	7
1.4 Scope of the Research	7
1.5 Significance of the Research	8
1.6 Thesis Organization	9
CHAPTER TWO: LITERATURE REVIEW	10
2.1 Introduction	10
2.2 A Brief History of Solar cell Development	10
2.3 Dye-Sensitized Solar Cells	13
2.3.1 The ZnO Nanorod and ZnO Nanorod/TiO ₂ composites Based Dye-Sensitized Solar Cells	16
2.4 Chapter Summary	29
CHAPTER THREE: METHODOLOGY	30
3.1 Introduction	30
3.2 Substrate Cleaning	33
3.3 Fabrication of ZnO Based Dye-sensitized Solar Cells	34

3.3.1	Preparation of Sn-doped ZnO Seed Layer	34
3.3.2	Preparation of Aligned ZnO Nanorod on Sn-doped ZnO Seed layer at Different Sn Concentrations	37
3.3.2.1	<i>Fabrication of Dye-sensitized Solar Cells using Aligned ZnO Nanorod at different Sn Concentrations</i>	39
3.3.3	Preparation of Aligned ZnO Nanorod on Sn-doped ZnO Seed layer at Different Zinc Acetate Solution Concentrations	41
3.3.3.1	<i>Fabrication of Dye-sensitized Solar Cells using Aligned ZnO Nanorod at different Zinc Acetate Solution Concentrations</i>	43
3.4	Fabrication of ZnO/TiO ₂ Based Dye-sensitized Solar Cells	45
3.4.1	Preparation of Nanostructured TiO ₂ Thin Films at Different deposition Frequencies	46
3.4.2	Preparation of Nano-composited Aligned ZnO nanorod/TiO ₂ Thin Films at Different Deposition Frequencies	47
3.4.2.1	<i>Fabrication of DSSCs Using Nano-composited Aligned ZnO Nanorod/TiO₂ at Different Deposition Frequencies</i>	49
3.4.3	Preparation of Nanostructured TiO ₂ :Nb Thin Films at Different Nb Concentrations	52
3.4.4	Preparation of Nano-Composited Aligned ZnO nanorod/TiO ₂ :Nb Thin Films at Different Nb Concentrations	53
3.4.4.1	<i>Fabrication of DSSCs Using Nano-composited Aligned ZnO Nanorod/TiO₂:Nb at Different Nb Concentrations</i>	55
3.5	Characterization Methods	57
3.5.1	Structural Properties	57
3.5.1.1	<i>Field Emission Scanning Electron Microscopy (FESEM)</i>	57
3.5.1.2	<i>Atomic Force Microscopy (AFM)</i>	57
3.5.1.3	<i>X-ray Diffraction (XRD)</i>	58
3.5.1.4	<i>Thickness Profilometry</i>	58
3.5.2	Optical Properties	58