## UNIVERSITI TEKNOLOGI MARA

# PREDICTION OF SHEAR CAPACITY OF CONCRETE BEAMS REINFORCED WITH GLASS FIBRE REINFORCED POLYMER (GFRP) BARS

NOOR AZLINA BINTI ABDUL HAMID

Thesis submitted in fulfilment of the requirements for the degree of **Doctor of Philosophy** 

**Faculty of Civil Engineering** 

November 2017

### ABSTRACT

Steel reinforcement bars are one of the most common reinforcement materials used in concrete structures for many decades due to their high tensile strength and modulus of elasticity. Moreover, its ability to withstand stress when subjected to high tensile loads leads to its high demand in the construction industry. However, the service life of steel reinforcement bars is often shortened due to corrosion especially when they are exposed to aggressive environmental conditions. Hence, the use of noncorrosive material such as Fibre Reinforced Polymer (FRP) as an alternative to reinforcement materials is recommended in this study. Compared to steel reinforcement, FRP reinforcement also offers excellent performance in terms of tensile strength and weight. Among the many types of FRP available, Glass Fibre Reinforced Polymer (GFRP) appears to be the most affordable compared to other types of FRP reinforcement such as Carbon Fibre Reinforced Polymer (CFRP) and Aramid Fibre Reinforced Polymer (AFRP). However, there is still a lack of information on the shear behaviour of concrete beams reinforced with GFRP bars. Furthermore, shear failure is more dangerous as it can occur abruptly without any warning. It has been reported that beams reinforced with longitudinal GFRP bars experienced lower shear strength compared to concrete beams reinforced with the same areas of longitudinal steel bars due to the low modulus elasticity of FRP bars. In addition, limited studies had reported the contribution of shear reinforcement in preventing sudden shear failure of concrete beams reinforced with GFRP bars. Thus, in this study, the investigation on the shear behaviour of concrete beams reinforced with GFRP bars was carried out. The study comprised of experimental and analytical investigation and numerical modelling. Eight concrete beams reinforced with steel bars (control beam) and sixteen beams reinforced with GFRP bars were tested. Three major variables namely tensile reinforcement ratio, shear span ratio and stirrup spacing were investigated. Analytical analysis using the ATENA software was used to simulate and analyse the response of the tested beams. The experimental results were also used to develop the shear strength design equation, V<sub>c</sub> for concrete beams reinforced with GFRP bars. The results of this study showed that beams reinforced with GFRP bars which contained steel stirrups resulted in a higher shear load capacity and less brittle failure. Increasing the reinforcement ratio up to 0.8% in combination with closer stirrup spacing of 50 mm within a shear span ratio of less than 2.5 significantly increased the ultimate shear load of the beam up to 35%. In addition, higher tensile strain was clearly detected at the support of the beams reinforced with GFRP bars compared to the beams reinforced with steel bars. Based on numerical analysis results, reasonable accuracy in terms of ultimate shear load, load-deflection relationship, strain and crack patterns was obtained. Additionally, the new shear strength equations predicted the shear capacity of the beams reinforced with GFRP bars well. The mean ratio, standard deviation and coefficient of variation for the proposed equation were 1.13, 0.19 and 17% respectively.

### ACKNOWLEDGEMENT

First and foremost in the name of Allah SWT., the most Gracious and Merciful, all praises to Allah for giving me the opportunity in completing my challenging PhD journey successfully. I offer my special appreciation to my main supervisor, Professor Dr. Azmi Ibrahim for his supervision, encouragement and guidance. He has provided me with the comfort environment and facilities throughout my research project. I am grateful to both of my co-supervisors, Ir. Dr. Rendy Thamrin and Datin Sri Prof. Dr. Hanizah for their understanding and support in completing this thesis. Dr. Rendy Thamrin has always giving me the ideas and knowledge to carry out my research work, which I am greatly indebted. For Datin Sri Prof. Dr. Hanizah, your kindness and guidance means a lot to me.

I would like to thank to all laboratory technicians at the Concrete and Heavy Structural Laboratory of the Faculty of Civil Engineering, Universiti Teknologi MARA, Shah Alam and Faculty of Civil and Environmental Engineering, Universiti Tun Hussein Onn Malaysia, Batu Pahat for their assistance and effort in handling the equipment and facilities during the experimental works.

My special thanks to all my friends, family members and my parents; Abdul Hamid Bin Sirat and for their endless love, prayers and encouragement throughout these challenging journey.

Finally, my deepest gratitude to my beloved husband, Muniri Bin Arsad for his prayers, encouragement and always by my side, your endless love means a lot to me. Also, to my children; Hadiff, Haira and Hasya, thanks for being a good child and I love you so much.

## **TABLE OF CONTENTS**

Page

CONFIRMATION BY PANEL OF EXAMINERS	ii
AUTHOR'S DECLARATION	iii
ABSTRACT	iv
ACKNOWLEDGEMENT	v
TABLE OF CONTENTS	vi
LIST OF TABLES	Х
LIST OF FIGURES	xii
LIST OF SYMBOLS	xvii
LIST OF ABBREVIATIONS	XX
CHAPTER ONE: INTRODUCTION	1
1.1 Introduction	1
1.2 Problem Statement	4
1.3 Objective Of Study	7
1.4 Scope of Study	8
1.5 Layout of Thesis	10
CHAPTER TWO: LITERATURE REVIEW	12
2.1 Introduction	12
2.2 Shear Mechanism	13
2.2.1 Reinforced Concrete (RC) Beams without Shear Reinforcement	13
2.2.2 Pre-cracking Phase	14
2.2.3 Post-cracking Phase	17
2.3 Factors Affecting Shear Behavior	20
2.4 Shear Failure Modes	21
2.5 Shear Design Provisions of Concrete Beams without Shear Reinforcement	25
2.5.1 British Standard Code (BS 8110-1: 1997)	26

## CHAPTER ONE INTRODUCTION

#### **1.1 INTRODUCTION**

Advanced Polymer Composites (APC) materials or formerly known as Fibre Reinforced Polymer (FRP) represents one of the most promising new reinforcing materials used in the construction industries. At first, the applications of FRP are predominately in the aerospace and off-shore industries. However, in the last four decades the potential advantage of FRP as an alternative building material has commenced in civil and structural engineering. In the 1970s, the use of FRP had been accepted for the construction of buildings since this material had been fully made from polymer composites. From 1990s until today, the trend in Figure 1.1 shows that polymer composites are used in the form of a combination of FRP with conventional reinforcement materials particularly under rehabilitation works of existing structures, and also for new structures.

Mainly due to corrosion problem found in steel bars of reinforced concrete (RC), structural engineers started to introduce FRP rebars as substitute to this traditional reinforcement material. Steel rebars embedded in concrete structures are protected by high alkalinity of the concrete (ph > 10) and they are surrounded by concrete cover against corrosive agents such as chloride ions (CI<sup>-</sup>), moisture (H<sub>2</sub>O) and air (O<sub>2</sub>). However, the durability of concrete is normally limited. Moreover, the concrete is always exposed to an aggressive environment that leads to carbonation process causing reduction of concrete alkalinity which eventually resulting in the corrosion of steel rebars. Some previous studies pointed out that the corroded reinforcement significantly affects the strength capacities and performance of RC beams (Capozucca 1995; Rodriguez et al. 1997). Therefore, high maintenance cost of repair work for rehabilitation or steel reinforcement replacement is indispensable to overcome corrosion problem.