UNIVERSITI TEKNOLOGI MARA

DURABLE PRESS FINISH WITH QUALITY REFERENCE FOR COTTON, VISCOSE RAYON AND THEIR BLENDS WITH POLYESTER

SALMIAH MOHD. NOR

Thesis submitted in fulfillment of the requirements for the degree of **Doctor of Philosophy**

Faculty of Applied Sciences

December 2010

ABSTRACT

In the preliminary study of Durable Press finish, ten new formulations of DP1 to DP10 were applied on light weight cotton fabric, by the pad-dry-cure method in the laboratory. The finishing solution consisted of Durable Press agent containing the alky! modified dihydroxy ethylene urea/melamine formaldehyde derivative, magnesium chloride, acetic acid and two softeners of functional polysiloxane active groups. The fabric was impregnated into the solution, padded and dried at 135°C for 30 minutes. Then it was cured at 140°C for five minutes. The finished fabric was tested and analyzed statistically for weight, wrinkle recovery angle (WRA), appearance, stiffness, drapability, abrasion resistance, breaking strength and tearing strength to decide on four formulations for trial run in the manufacturing process at the textile mill. The selected formulations with good Durable Press performances were DP7, DP8, DP9 and DP10. These formulations were applied on four fabrics of light and medium weight cotton and polyester/cotton (65/35) after dyeing. At the mill, the formulations and application method of DP7, DP8, DP9 and DP10, were the same as in the preliminary study, with an additional process of compressive shrinkage after curing. The finished fabrics were analyzed to decide on ONE optimum formulation of Durable Press finish, which was then applied on four other fabrics of light and medium weight viscose rayon and polyester/viscose rayon (65/35). This ONE formulation was DP10, and it now becomes the Durable Press formulation for all eight fabrics.

The DP10 was formulated with vat dye in the single bath process of combined dyeing and finishing of DPV1 to DPV8 in the laboratory. From these eight formulations, three were selected for trial run in the textile mill, on eight fabrics to decide one optimum formulation. The three selected formulations were DPV6, DPV7 and DPV8, and from these, the optimum ONE was DPV8.

A quality measurement of Durable Press Reference (DPR), a novelty of this research was developed using the properties of wrinkle resistance and draping quality of all finished fabrics. It is a formula to calculate objectively the Durable Press performances of fabrics. The DPR for the eight fabrics is 3.39 to 7.53, differently for each fabric of different fiber content.

DP10 and DPV8 fabrics resist flaming, have good color appearance and fastness, dimensionally stable and are durable to repeated home launderings. The formaldehyde released from fabrics complies with the OSHA health requirement, except for the viscose rayon fabrics. Durable Press finishes of DP10 and DPV8, overall have enhanced FAST evaluation of fabrics, with warning statements for tailoring noted for each fabric.

ACKNOWLEDGEMENTS

I would like to express my sincere appreciation and gratitude to my supervisor, Prof. Dr. Wan Yunus Wan Ahmad for his guidance and encouragement throughout my study. My appreciation and thank you also go to my co-supervisor, Prof. Dr. Jamil Salleh for his advice and support.

My heartfelt appreciation and gratitude go to Tuan Hj. Abdul Hamid Majid and Encik Shamsu Bahari Abu Bakar of the Textile Division, AMDB Berhad for allowing me to carry out this joint research project and for their technical support. I would also like to extend my appreciation to all the staff of the Dyeing and Finishing Mill, as well as the Textile Testing Laboratory of AMDB Berhad for their co-operation and support throughout my study.

My appreciation also goes to the Institute of Research, Development and Commercialization (IRDC), now known as the Research Management Institute (RMI) of the Universiti Teknologi MARA (UiTM) for financially supporting the research project. I am also grateful to the Dean of the Faculty of Applied Sciences, UiTM for his support of my study. My appreciation and thank you also go to the Head of the Textile Technology Programme, as well as all the staff and research assistants of the programme for their support and co-operation.

I would also like to extend my thank you to Assoc. Prof. Dr. Nora Zakaria, Assoc. Prof. Halilah Haron and Assoc. Prof. Dr. Razidah Ismail for their constructive advice and assistance in the analysis of the research results. My thank you also goes to all others who have directly or indirectly helping me with the research project.

Last but not least, my deepest appreciation goes to my dearest husband, Jaya Abdullah and my three children, Joana, Olina and Adam for their love, support and understanding given to me. I am also indebted to both of my late parents who had always encouraged my studies.

TABLE OF CONTENTS

			rage				
TIT	LE PAG	E					
CAN	TALLO	'E'S DECLARATION					
ABSTRACT ACKNOWLEDGEMENTS TABLE OF CONTENTS							
				LIST	Г OF ТА	ABLES	x
				LIS	Г OF FI	GURES	xvii
LIST	Г OF AI	BREVIATIONS	xxi				
CHA	APTER :	1: INTRODUCTION					
1.1	Proble	em Statement	3				
1.2	Assun	ptions and Limitations of the Research	6				
1.3	Object	tives of the Research	8				
CHA	APTER 2	2: LITERATURE REVIEW					
2.1	Histor	History of Durable Press Finish					
2.2	Fabric	cs for Durable Press Finish	12				
2.3	Durat	ole Press Finish and Wrinkling of Cellulose Fibers	15				
2.4	Durat	Durable Press Finish					
	2.4.1	Non-formaldehyde Durable Press Finish	17				
	2.4.2	Formaldehyde Durable Press Finish	20				
		2.4.2.1 Modified DMDHEU	25				
		2.4.2.2 Properties of DMDHEU Finished Fabrics	28				
2.5	Application Methods for Durable Press Finish						
	2.5.1	Pad-dry-cure Method	31				
	2.5.2	Compressive Shrinkage Process	32				
2.6	Durat	ole Press Quality Measurement	33				

CHAPTER 3: MATERIALS AND METHODS

3.1	Fabrics		35	
3.2	Durable Press Chemicals			
3.3	Durable Press Finish Formulation and Application Method			
3.4	Fabric Testing			
	3.4.1	Weight	44	
	3.4.2	Wrinkle Recovery Angle	44	
	3.4.3	Appearance	46	
	3.4.4	Stiffness	46	
	3.4.5	Drapability	47	
	3.4.6	Abrasion Resistance	47	
	3.4.7	Breaking Strength	48	
	3.4.8	Tearing Strength	48	
	3.4.9	Formaldehyde Content	48	
	3.4.10	Flame Resistance	49	
	3.4.11	Color Appearance	49	
	3.4.12	Colorfastness to Washing	50	
	3.4.13	Colorfastness to Perspiration	50	
	3.4.14	Colorfastness to Rubbing/Crocking	50	
	3.4.15	Colorfastness to Light	50	
	3.4.16	Dimensional Stability	51	
	3.4.17	Effects of Repeated Home Launderings	51	
	3.4.18	FAST Evaluation	52	
3.5	Statistical Analysis of Fabric Properties			
3.6	Durable	Press Reference (DPR)	57	
CHA	PTER 4:	PRELIMINARY STUDY OF DURABLE PRESS FINISH		

4 .1	Ten New Formulations of Durable Press Finish	60
4.2	Results and Discussion of Light Weight Cotton Fabric of DP1 to DP10	63