

**SYNTHESIS AND CHARACTERIZATION OF
MESOPOROUS ZEOLITE FROM COAL FLY
ASH FOR BIO-OIL PRODUCTION**

NUR IZZATI BINTI MAT FAZLI

**BACHELOR OF CHEMICAL ENGINEERING
(ENVIRONMENT) WITH HONOURS**

UNIVERSITI TEKNOLOGI MARA

2022

**SYNTHESIS AND CHARACTERIZATION OF
MESOPOROUS ZEOLITE FROM COAL FLY ASH FOR
BIO-OIL PRODUCTION**

By

NUR IZZATI BINTI MAT FAZLI

This report is submitted in partial fulfillment of the requirements
needed for the award of
Bachelor of Chemical Engineering (Environment) with Honours

**CENTRE FOR CHEMICAL ENGINEERING STUDIES
UNIVERSITI TEKNOLOGI MARA**

AUG 2022

ACKNOWLEDGEMENT

In the name of Allah S.W.T my greatest appreciation and thanks to Him for rewarding me lots of perseverance and patience in enduring lots of obstacles throughout this Final Year Project II. I would like to express my gratitude toward my supervisor, Dr. Hamizura binti Hassan for her help in guiding me and giving me valuable constructive criticism. Her willingness in helping and sharing her knowledge has been such a help for me in doing and finishing my report for the Final Year Project Report II. The willingness of her to spend their precious time for the consultation during the project is deeply appreciated. Next, I would like to show my gratitude toward the final year project II coordinator, Ir. Dr. Noorzalila Muhammad Niza for coordinating all the CEV652 related activities throughout the academic session smoothly. Finally, I would like to thank my parents and my friends for their help and encouragement which is very helpful for me in completing this report.

TABLE OF CONTENTS

	PAGE
AUTHOR'S DECLARATION	i
SUPERVISOR'S CERTIFICATION	ii
COORDINATOR'S CERTIFICATION	iii
ACKNOWLEDGEMENT	iv
TABLE OF CONTENTS	v
LIST OF TABLES	vii
LIST OF FIGURES	viii
LIST OF PLATES	x
LIST OF SYMBOLS	xi
LIST OF ABBREVIATIONS	xii
ABSTRACT	xiii
CHAPTER ONE INTRODUCTION	1
1.1 Research Background	1
1.2 Problem Statement	3
1.3 Objectives	5
1.4 Scope of Work	5
CHAPTER TWO LITERATURE REVIEW	6
2.1 Catalytic Co-Pyrolysis	6
2.1.1 Coal Fly Ash	7
2.2 Zeolite Synthesis	8
2.2.1 Role of Zeolite	9
2.2.2 Early proposed mechanisms of zeolite synthesis (Solution-mediated transformation mechanism)	10
2.3 Method zeolite synthesis from coal fly ash	11
2.3.1 Direct Hydrothermal Method	12
2.3.2 Two-step Hydrothermal Method	13
2.3.3 Alkali Fusion-assisted Hydrothermal Method	14

ABSTRACT

Coal fly ash, which contains the high amount of silica and alumina content, discharged from the coal electric power plants is one of the by-product of thermal power generation that could be used as a precursor for the production of zeolite-based catalysts. Coal fly ash could be a more cost-effective alternative to synthetic zeolite since it is abundant around the world. Coal fly ash was used to synthesize mesoporous zeolite by alkali fusion followed by hydrothermal treatment. This study focuses on the synthesis and characterization of mesoporous zeolite. The raw materials were treated with alkaline using hydrothermal and fusion methods. Hydrothermal was performed at a temperature of 160 °C for 24 h in a stainless steel autoclave. The synthesized zeolite was characterized using various techniques such as Fourier Transform Infrared (FTIR), Scanning Electron Microscopy-Energy Dispersive X-ray Analysis (SEM-EDX) and Brunauer, Emmett, and Teller (BET) method for surface area measurement, pore volume and pore size. The results indicated that the synthesised zeolite derived from coal fly ash demonstrated the characteristics of zeolite-like materials. The maximum surface area of the synthesised zeolite was found to be 42.2719 m²/g with high purity. The SEM observations of grain shapes revealed that the synthesised zeolite was composed of isometric and octahedral crystals proving that the synthesis process was successful. The existence of the two most intense bands for zeolites which was the internal tetrahedron vibrations of Si-O-Si and Si-O-Al implies zeolite formation.