

**A STUDY ON THE EFFECT OF MECHANICAL PROPERTIES AND  
RHEOLOGICAL BEHAVIOUR OF POLYPROPYLENE REINFORCED  
MONTMORILLONITE**

**NORMUHAIZAH BINTIMOHD ZAIN**

**(2006131637)**

A thesis proposal submitted in partial fulfillment of the requirements for the award of  
Bachelor Engineering (Hons) (Mechanical)

**Faculty of Mechanical Engineering  
Universiti Teknologi MARA (UiTM)**

**MAY 2010**

## ACKNOWLEDGEMENT

First of all, I would like to express my thankfulness to Allah, Most Greatest Most Merciful for given me a time and a good health to complete this final project successfully. I would like to express my greatest appreciation to my final project advisor, Prof. Madya Nor Aini Wahab for her valuable advice, guideline, support and willing in sharing a knowledge towards completion of this final project.

I also would like to acknowledge technician especially Mr Naziman , Technician of Composite Laboratory, Technician of Strength Laboratory, Mr Norazman, Technician of Material Laboratory, Mr. Rahimi, and Technician of Polymer Laboratory, and all the person involve who has given their knowledge, expertise and morale supports in making this project a success. I would also like to thank UiTM for providing me the venue as well as materials and machineries to complete this project.

This project gives me a lot benefit for me as future engineer. Last but not least, I am greatly indebted to my family and my friends for their understanding, patience and support during the entire period of my study, thank you for all.

## ABSTRACT

This research focused on the mechanical properties of polypropylene (PP) reinforced montmorillonite (MMT). The aim of this research is to determine the mechanical properties of PP/MMT nanocomposite with different concentration (2 wt%, 4 wt%, 6 wt% , 8 wt% and 10 wt%) of MMT. PP and MMT were mix by using Dispersion Mixer. The material was mixed at temperature 190°C. After that, the material was fabricated by using hot press with 190°C for both upper and lower compressor. Mechanical properties of the sample were evaluated by tensile test, impact test, and three point bending test according to BS EN ISO 527, BS EN 60811 and BS 6319 respectively. From the tensile test, the result obtained shown that the sample of 2wt.% and for impact test shown 6wt.% of clay loading which has the better mechanical properties. The rheological behavior also determined. All the concentration have pseudoplastic, but the better pseudoplastic is 8wt.% of loading clay.

## TABLE OF CONTENTS

<b>CONTENTS</b>	<b>PAGE</b>
TITLE PAGE	i
DECLARATION	ii
DEDICATION	iv
ACKNOWLEDGMENT	vi
ABSTRACT	vii
TABLE OF CONTENT	viii
LIST OF FIGURES	xii
LIST OF TABLES	xiv
LIST OF ABBREVIATIONS AND SYMBOLS	xv

### CHAPTER I: INTRODUCTION

1.0 Introduction	1
1.1 Objectives of the Study	2
1.2 Scopes of the Study	3
1.3 Significance of the Study	3
1.4 Problem statement	4

## CHAPTER II: LITERATURE REVIEW

2.1	Introduction	5
2.2	Material Background	
2.2.1	Polypropylene	8
2.2.2	Montmorillonite	11
2.2.2.1	Structure of Layered Silicates	12
2.2.3	Microstructure of nanocomposite	13
a)	Phase separated microcomposites	13
b)	Intercalated nanocomposites	13
c)	Exfoliated nanocomposites:	14
2.2.4	Properties of Nanocomposites	15
2.2.5	Application of nanocomposite	15
2.2.6	Polymer nanocomposite	16
2.2.6.1	Types of nanoparticles	18
a)	Termoset nanocomposite	18
b)	Thermoplastic Nanocomposites	18
2.2.6.2	Properties of Polymer Nanocomposite	19
2.2.6.2.1	Mechanical Properties	19
a)	Modulus and the Load-Carrying Capability of Nanofillers	19
b)	Toughness	21
2.2.7	Effect of filler on the Properties of Polypropylene Nanocomposites	22